

Obligation Keeps Excellence

▶ International Sales Hotline
0086-731-27577393

OKE Precision Cutting Tools Co., Ltd.

Head Office Add: Chuangye Rd, Chuangye Park for SMEs, Yanling County, Zhuzhou, Hunan, China.
Branch Office Add: #8, Chuangye Rd, Lusong Area, Zhuzhou, Hunan, China.
Tel: +86 0733-22673968 Fax: +86 0731-22673961
E-mail: oke_info@oke-carbide.com info@oke-carbide.com
Web: www.oke-carbide.com

OKE reserves the final interpretation of this booklet


OKE 欧科亿 Cutting Tools Catalog


2023

OKE 欧科亿

股票代码: 688308

CUTTING TOOLS CATALOG





Cutting Tools

A

Turning Tools

B

Milling Tools

C

Drilling Tools

D

Solid End Mill

E

General Technical Guide


Cutting Tools for Small Parts Machining

PVD stainless steel
new grade for turning
machining

OP1415

NEW

Performance is
improved by 30%




Front sweep tool

Precision small parts processing
4 types of cutting tools (front sweep, back sweep, cutting, grooving);
Stable product performance, used for automatic processing

JF chipbreaker

Better chip handling capacity, suitable for small cutting depth, large feed processing conditions
Excellent cutting effect to obtain good workpiece surface quality




JU chipbreaker


Sharp cutting edge, small resistance, can be used for slender shaft processing
Long cutting edge, the maximum cutting depth is 4mm, high processing efficiency, can meet the demand of "one size fits all"

JY chipbreaker


Wide chipbreaker can ensure smooth cutting
Excellent chip handling capability can improve tool life and chip performance

Recommended machining parameter






Cermet turning grade
OKE6310



Efficient • Stable **New Generation**
CVD grade Products for Steel Turning



Steel

Finishing

-OPF

Special designed for steel finishing;
Unique design efficiently controls the form of chip and breaks chip;
Sharp cutting edge, smooth cutting;
Excellent surface quality.



-OTF

Special chip breaker structure makes excellent chip breaking even at small cutting depth.
Sharp cutting edge, cutting smoothly and quickly.

Semi-Finishing

-OPM

Negative chamfer designation gives blade good strength;
Double chipbreaker lands, makes bigger chip control range.



-OTM

Flat cutting edge design, good wear-resistance and breakage resistance.
Inclination angle combination structure can control the chip breaking direction efficiently.



Roughing

-OPR

Three-dimension designed with double rake angle, wide margin and negative chamfer;
Wonderful blade intensity gives a longer tool life time;
Suitable for steel roughing machining.



-OTR

Flat cutting edge with big rake angle, gives good wear-resistance.
Varying chip breaker depth design, good performance on chip breaking control.




Stainless Steel

Finishing

-OMF

Special designed rake angle and cutting edge inclination;
Sharp cutting edge, small cutting force;
Good machining surface quality.




-MSF

Three-dimension designed with double rake angle;
Sharp cutting edge and lower cutting resistance;
Efficiently solved build up edge, work hardening and other machining problems.
Cutting edge inclination designation is good to control chip flow direction and obtains excellent Surface quality.



-OTF

Special chip breaker structure makes excellent chip breaking even at small cutting depth.
Sharp cutting edge, cutting smoothly and quickly.



Semi-Finishing

-OMM

Special chipbreaker design to keep cutting edge sharp and safe;
Good anti impact resistance;
Excellent tool life time;




-MF

Special chipbreaker design to keep both sharp cutting edge and increased blade intensity;
Efficiently solved break chip, high cutting temperature, sticking, work hardening and other machining problems.
It has very excellent efficiency



-OTM

Flat cutting edge design, good wear-resistance and breakage resistance.
Inclination angle combination structure can control the chip breaking direction efficiently.



Cast Iron

Finishing To Semi-Finishing

-OKM

Wide support surface for stable clamping and preventing chipping

Sharp cutting edge, improve workpiece surface quality

Excellent chipping resistance in continuous machining

High quality surface roughness



Roughing

-OKR

Wide support surface for stable clamping and preventing chipping

Optimized edge width for high-speed, high-feed machining

Excellent chipping resistance in interrupted machining

Improve machining stability and extend tool life



High Temperature Alloy

Semi-Finishing

-SMM

Three-dimensional groove design with large rake angle;

Sharp cutting edge and low cutting force;

Processing difficulties such as high temperature processing and work hardening;

Suitable for finishing of super-alloy materials.



-OSM

Effectively control chip curling and flow;

Sharp cutting edge, smooth quick cutting;



Proper edge strength gives a longer service life



Aluminum Alloy


-NL

Finishing To Roughing




Parting and Grooving

-OC



-MG



CVD

Grade	Hardness	Coating Type	Colour	Feature
OC2115	1530	CVD	Black	Low Cobalt content, and high cubic content carbide substrate combine with thick TiCN and Al ₂ O ₃ , treated by special after coating treatment, which gives insert wonderful wearing resistance. Preferred grade for semifinishing to finishing steel machining. ●
OC2125	1480	CVD	Black	Low Cobalt content, and high cubic content carbide substrate combine with thick TiCN and Al ₂ O ₃ , treated by special after coating treatment, which gives insert wonderful wearing resistance. Preferred grade for semifinishing to finishing steel machining. ●
OC2325	1480	CVD	Yellow	Medium cobalt content, and high cubic content carbide substrate combine with strong texture TiCN and Al ₂ O ₃ coating. After special treatment, it has wonderful abrasion resistance. ●
OC2325S	1480	CVD	Double color	Gradient hard alloy substrate with rich cubic phase content has better high temperature performance and plastic deformation resistance. The uniform dense and fine-grained coating has excellent wear resistance, and the special transition layer structure ensures the anti-peeling performance of the coating; The unique post-processing technology realizes a two-color marking layer and uniform compressive stress distribution, ensuring higher wear resistance and stability. It is suitable for turning of various steels and is the first choice for wear resistance. ●


CVD

Grade	Hardness	Coating Type	Colour	Feature
OC2425	1470	CVD	Double color	High cubic content gradient carbide substrate, gives good anti-deformation resistance and excellent high temperature performance. Dense and uniform ultra-fine-grained coating, providing excellent wear resistance, unique transition layer structure, to ensure the anti-peeling performance of the coating; unique post-processing technology, realizing two-color and beneficial compressive stress distribution, to achieve higher resistance Abrasiveness and stability. The substrate edge part adopts a unique "skeleton" structure, which achieves excellent cutting performance and good safety. The red hardness of the substrate is further improved by optimizing and adjusting the ratio of raw materials in the solid solution and the particle size of the raw materials. It is suitable for high-efficiency, light-interrupted machining of P10-P20 (medium and high carbon steel, low alloy steel), with a wider application range and better stability. ●
OC3210	1650	CVD	Double color	Fine-grained and high-hardened chemical coating, the substrate has good wear resistance, and achieves stability and long life in a wide range of processing fields. Gray cast iron, ductile iron machining (continuous, light interrupted conditions) Gray cast iron, ductile iron machining (small parts roughing) ●
OC3215	1580	CVD	Black	The medium-coarse substrate combine with thick TiCN and textured Al ₂ O ₃ , after special after coating treatment, it has outstanding wearing resistance. Suitable for high speed semi-finishing cast iron cutting under stable work condition. ●
OC3220	1600	CVD	Double color	MTCVD TiCN-Al ₂ O ₃ coating strengthened by fine-grained α-Al ₂ O ₃ film, the substrate is a kind of hard alloy with good toughness Gray cast iron, ductile iron machining (strong interrupted conditions) Gray cast iron, ductile iron machining (roughing, black skin conditions) ●
OC4315	1480	CVD	Gold	Medium Cobalt content, and high cubic content carbide substrate combine with thin TiCN and Al ₂ O ₃ , treated by special after coating treatment, which gives insert wonderful wearing resistance. Preferred grade for stainless steel turning at high speed. ●

PVD

Grade	Hardness	Coating Type	Colour	Feature
OP1030	1500	PVD	Gray	High Co content and ultra fine WC grain substrate, gives wonderful toughness, combines with PVD AlTiN coating, it has good strength and versatility. Suitable for steel and stainless steel milling and drilling. ● ●
OP1205	1650	PVD	Dark Purple	High Co content and ultra fine WC grain substrate, gives wonderful cutting edge strength, combines with good thermal stability silicon coating, it has very small coefficient of friction, and good nano hardness. Suitable for steel and stainless steel continue turning and threading. ● ●
OP1215	1560	PVD	Dark Purple	High Co content and fine WC grain substrate, gives wonderful cutting edge strength, combines with good thermal stability silicon coating, it has very small coefficient of friction, and good nano hardness. Good at stainless steel semi-finishing turning, parting and grooving processing. preferred grade for steel and stainless steel milling and drilling. ● ●
OP1315	1560	PVD	Gray	High Co content and fine WC grain substrate, gives wonderful cutting edge strength, combines with new AlTiN coating, it has very small coefficient of friction, high antioxidant temperature, and good nano hardness. Preferred grade for steel and stainless steel milling and drilling. ● ●


Grade	Hardness	Coating Type	Colour	Feature
OP1415	1550	PVD	Dark Purple	The coating has dense columnar crystals and small gaps between crystals, which can effectively improve the oxidation resistance and plastic deformation resistance; The lower the roughness of the coating surface, the lower the resistance and heat generated during cutting can be effectively reduced; The bonding force between the film layer and the substrate is strong, which reduces the abnormal cracking of the product and improves the service life of the tool. ●
OP1325	1580	PVD	Yellow	New material substrate has good anti wear resistance and anti impact resistance. Combining with multiple layers AlTiN coating, it has excellent adhesion between coating and substrate which improves tool life significantly. Suitable for general steel, and stainless steel milling. ● ●
OP1630	1520	PVD	Yellow	Newly upgraded coating technology, the new king of steel milling; Enhanced tip design, excellent impact resistance; Improved side, stable fit; With supporting development of steel products, the performance is better; ●
OP2202	1640	PVD	Gray	High Co content and ultra fine WC grain substrate, gives wonderful cutting edge strength, combines with PVD AlTiN coating, it has outstanding wearing resistance. Suitable for steel and cast iron slight milling. ● ●



A Turning Tools

a Turning Insert 001-058

b Turning Tools 059-140



ISO Turning Insert Naming Rules

Shape

C N M G 12 04 08 — OPM

A 	B 	C
D 	E 	H
K 	L 	M
O 	P 	R
S 	T 	T
V 	W 	Z

Chip Breaker and Hole

C N M G 12 04 08 — OPM

Symbol	Center Hole	Chip Breaker	Insert Profile	Symbol	Center Hole	Chip Breaker	Insert Profile
B	(Y)	(N)		N	(N)	(N)	
H	(Y)	(S)		R	(N)	(S)	
C	(Y)	(N)		F	(N)	(D)	
J	(Y)	(D)		A	(Y)	(N)	
W	(Y)	(N)		M	(Y)	(S)	
T	(Y)	(S)		G	(Y)	(D)	
Q	(Y)	(N)		X			
U	(Y)	(D)					

Clearance Angle

C N M G 12 04 08 — OPM

A 	B
C 	D
E 	F
G 	N
P 	O Others

Tolerance

C N M G 12 04 08 — OPM

Symbol	m(mm)	d=i.c. (mm)	s (mm)	(reference)M grade tolerance detail(according to shape, size.) Tolerance of insert nose height						
				Inscribed Circle	Regular Triangle	Square	80° Rhombus	55° Rhombus	35° Rhombus	Round
				6.35	±0.08	±0.08	±0.08	±0.11	±0.16	...
				9.525	±0.08	±0.08	±0.08	±0.11	±0.16	...
				12.7	±0.13	±0.13	±0.13	±0.15
A	±0.005	±0.025	±0.025	15.875	±0.15	±0.15	±0.15	±0.18
F	±0.005	±0.013	±0.025	19.05	±0.15	±0.15	±0.15	±0.18
C	±0.013	±0.025	±0.025	25.4	...	±0.18
H	±0.013	±0.013	±0.013	●Tolerance of Inscribed Circle						
E	±0.025	±0.025	±0.025	Inscribed Circle	Regular triangle	Square	80° Rhombus	55° Rhombus	35° Rhombus	Round
G	±0.025	±0.025	±0.13	6.35	±0.05	±0.05	±0.05	±0.05	±0.05	
J	±0.005	±0.05-±0.13	±0.025	6.35	±0.05	±0.05	±0.05	±0.05	±0.05	
K	±0.013	±0.05-±0.13	±0.025	9.525	±0.05	±0.05	±0.05	±0.05	±0.05	±0.05
L	±0.025	±0.05-±0.13	±0.025	12.7	±0.08	±0.08	±0.08	±0.08	...	±0.08
M	±0.08-±0.18	±0.05-±0.13	±0.13	15.875	±0.1	±0.1	±0.10	±0.10	...	±0.1
N	±0.08-±0.18	±0.05-±0.13	±0.025	19.05	±0.1	±0.1	±0.10	±0.10	...	±0.1
U	±0.13-±0.38	±0.08-±0.25	±0.13	25.4	±0.13	±0.13

ISO Turning Insert Naming Rules

Cutting Edge Length

C N M G 12 04 08 — OPM

Inscribed Circle diameter(mm)	Insert Shape							
	C	D	R	S	T	V	W	K
3.97					06			
5			05					
5.56					09			
6			06					
6.35	06	07			11	11		
8			08					
9.525	09	11	09	09	16	16	06	16
10			10					
12			12					
12.7	12	15	12	12	22	22	08	
15.875	16		15	15	27			
16			19	16				
19.05	19		19	19	33			
20			20					
25	25	25	25					
25.4			25	25				
31.75			31					
32			32					

Thickness

C N M G 12 04 08 — OPM

Symbol	Thickness(mm)
00	0.79
T0	0.99
01	1.59
T1	1.98
02	2.38
T2	2.58
03	3.18
T3	3.97
04	4.76
T4	4.96
05	5.56
T5	5.95
06	6.35
T6	6.75
07	7.94
09	9.52
T9	9.72
11	11.11
12	12.7

The Height Between Insert Bottom And Nose

Corner Radius

C N M G 12 04 08 — OPM

Symbol	Corner Radius (mm)
00	
02	0.2
04	0.4
08	0.8
12	1.2
16	1.6
20	2
24	2.4
32	3.2
X	其它 Special

Diameter Dimension Round Insert

Chip Breaker

C N M G 12 04 08 — OPM

OPF	OPM	OPR	OMF	OMM
MF	MSF	OTF	OTM	OTR
OKM	OKR	OSM	SMM	NL

Inserts Overview

CNMG-OPF	CNMG-OMF	CNMG-MSF	CNMG-OPM	CNMG-OMM	CNMG-MF
					
P10	P10	P10	P10	P11	P11
EdgeLength 12.9	EdgeLength 12.9	EdgeLength 9.7 12.9	EdgeLength 12.9 16.1 19.3	EdgeLength 12.9 16.1	EdgeLength 9.7 12.9 16.1
CNMG-OKM	CNMG-OSM	CNMG-SMM	CNMG-OPR	CNMG-OMR	CNMG-OKR
					
P11	P11	P11	P12	P12	P12
EdgeLength 12.9	EdgeLength 12.9	EdgeLength 12.9	EdgeLength 12.9 16.1 19.3	EdgeLength 12.9	EdgeLength 12.9 16.1
CNMM-PR	CNMM-PR	CNMG	CNMA	DNMG-OPF	DNMG-OMF
					
P12	P12	P13	P13	P14	P14
EdgeLength 19.3	EdgeLength 25.8	EdgeLength 12.7 16.1 19.3	EdgeLength 12.7 16.1 19.3	EdgeLength 11.6 15.5	EdgeLength 15.5
DNMG-MSF	DNMG-OPM	DNMG-OMM	DNMG-MF	DNMG-OKM	DNMG-OSM
					
P14	P14	P14	P14	P15	P15
EdgeLength 11.6 15.5	EdgeLength 11.6 15.5	EdgeLength 11.6 15.5	EdgeLength 11.6 15.5	EdgeLength 15.5	EdgeLength 15.5
DNMG-OPR	DNMG-OKR	DNMG	DNMA	SNMG-OPF	SNMG-OMF
					
P15	P15	P15	P15	P16	P16
EdgeLength 15.5	EdgeLength 15.5	EdgeLength 11.6 15.5	EdgeLength 15.5	EdgeLength 12.7	EdgeLength 12.7
SNMG-OPM	SNMG-OMM	SNMG-MF	SNMG-OKM	SNMG-OSM	SNMG-SMM
					
P16	P16	P16	P17	P17	P17
EdgeLength 12.7 15.875 19.05	EdgeLength 12.7 15.875	EdgeLength 12.7	EdgeLength 12.7	EdgeLength 12.7	EdgeLength 12.7

Inserts Overview

SNMG-OPR	SNMM-OPR	SNMG-OKR	SNMM-PR	SNMG	SNMA
					
P17	P17	P17	P18	P18	P18
EdgeLength 12.7 15.875 19.05	EdgeLength 19.05	EdgeLength 12.7 15.875 19.05	EdgeLength 25.4	EdgeLength 12.7 15.875 19.05 25.4	EdgeLength 12.7
TNMG-OPF	TNMG-OMF	TNMG-MSF	TNMG-OPM	TNMG-OMM	TNMG-MF
					
P19	P19	P19	P20	P20	P20
EdgeLength 16.5	EdgeLength 16.5	EdgeLength 16.5	EdgeLength 16.5 22	EdgeLength 16.5 22	EdgeLength 16.5 22
TNMG8-OKM	TNMG-SMM	TNMG-OPR	TNMG-OMR	TNMG-OKR	TNMG
					
P20	P20	P21	P21	P21	P22
EdgeLength 16.5	EdgeLength 16.5	EdgeLength 16.5 22 27.5	EdgeLength 16.5	EdgeLength 16.5	EdgeLength 16.5 22
TNMA	VNMG-OPF	VNMG-MSF	VNMG-OPM	VNMG-OMM	VNMG-MF
					
P22	P23	P23	P23	P23	P23
EdgeLength 16.5 22	EdgeLength 16.6	EdgeLength 16.6	EdgeLength 16.6	EdgeLength 16.6	EdgeLength 16.6
VNMG-OKM	VNMG-SMM	VNMG-OPR	VNMG-OKR	VNMG	VNMA
					
P24	P24	P25	P25	P25	P25
EdgeLength 16.6	EdgeLength 16.6	EdgeLength 16.6	EdgeLength 16.6	EdgeLength 16.6	EdgeLength 16.6
WNMG-OPF	WNMG-OMF	WNMG-MSF	WNMG-OPM	WNMG-OMM	WNMG8-MF
					
P26	P26	P26	P26	P26	P26
EdgeLength 6.5	EdgeLength 6.5 8.7	EdgeLength 6.5 8.7	EdgeLength 6.5 8.7	EdgeLength 6.5 8.7	EdgeLength 6.5 8.7

Inserts Overview

WNMG-OKM	WNMG-SMM	WNMG-OPR	WNMG-OMR	WNMG-OKR	WNMG
					
EdgeLength 8.7	EdgeLength 8.7	EdgeLength 8.7	EdgeLength 8.7	EdgeLength 8.7	EdgeLength 8.7
WNMA	CCMT-OTF	CCMT-MSF	CCMT-OTM	CCMT-OTR	DCMT-OTF
					
EdgeLength 8.7	EdgeLength 6.4 9.7 12.9	EdgeLength 6.4 9.7 12.9	EdgeLength 6.4 9.7 12.9	EdgeLength 6.4 9.7 12.9	EdgeLength 7.8 11.6
DCMT-MSF	DCMT-OTM	DCMT-OTR	RCMXMO	RCMXMO-Q	RCMTMO
					
EdgeLength 7.8 11.6	EdgeLength 7.8 11.6	EdgeLength 11.6	EdgeLength 8.0	EdgeLength 12 16 20 25 32	EdgeLength 8.0
RCMTMO-Q	SCMT-OTF	SCMT-OTM	SCMT-OTR	TCMT-OTF	TCMT-OTM
					
EdgeLength 16	EdgeLength 9.525 12.7	EdgeLength 9.525 12.7	EdgeLength 9.525 12.7	EdgeLength 11 16.5	EdgeLength 9.6 11 16.5
TCMT-OTR	VBMT-OTF	VBMT-OTM	VBMT-OMM	VBMT-OSM	VBMT-OTR
					
EdgeLength 16.5 22	EdgeLength 16.5	EdgeLength 11 16.5	EdgeLength 16.5	EdgeLength 16.5	EdgeLength 16.5
VCMT-OTF	VCMT-OTM	VCMT-OSM	TPGH	KNUX	175.32
					
EdgeLength 11 16.5	EdgeLength 16.5	EdgeLength 16.5	EdgeLength 6.4 8.2 9.6 11	EdgeLength 16.2	EdgeLength 19.1

Inserts Overview

175.32

EdgeLength 19.1

Insert for Aluminum

CCGX-NL	DCGX-NL	RCGT-NL	SCGX-NL	TCGX-NL	VCGX-NL
					
EdgeLength 6.4 9.7 12.9	EdgeLength 7.8 11.6	EdgeLength 6.5 8.7	EdgeLength 9.525 12.7	EdgeLength 9.6 11 16.5	EdgeLength 11 16.5 22

Cermet Inserts







CNMG-SAL	TNMG-SAL	VNMG-SAL	WNM-SAL
			
EdgeLength 12.9	EdgeLength 16.5	EdgeLength 16.6	EdgeLength 8.7







Parting and Grooving Inserts

Q□□D-MG	Q□□W-OC
	
EdgeLength 2.5 3 4 5 6	EdgeLength 2 2.5 3 4 5

Inserts Overview

Threading Insert

60° general pitch threads	55° general pitch threads	ISO metric threads	Unified thread (American standard thread)	Whitworth threads	British standard taper pipe threads
 P47	 P48	 P49	 P50	 P51	 P52

NPT American standard taper pipe threads	UNJ American standard aerospace and aviation threads	30° DIN405 round threads	Petroleum pipeline threads	30° ISO metric threading insert	29° American standard ACME threads
 P53	 P54	 P55	 P56	 P56	 P57

29° American standard STACME threads
 P58


Chipbreaker Introduction Chart

ISO Code	P	P/M	M	K	N	S
Finishing	OPF OPF Chip Breaker: Suitable for finishing ISO P material.	OTF OTF Chip Breaker: Suitable for finishing ISO P and M material.	OMF OMF Chip Breaker: Suitable for finishing ISO M material.			
			MSF MSF Chip Breaker: Suitable for finishing ISO M material.			
Semi Finishing	OPM OPM Chip Breaker: Suitable for semi-finishing ISO P material.	OTM OTM Chip Breaker: Suitable for semi-finishing ISO P and M material.	MF MF Chip Breaker: Suitable for semi-finishing ISO M material.	OKM Suitable for gray cast iron, nodular cast iron continuous/slight interrupt cutting		SMM Suitable for long time continuous semi-finishing to finishing cutting.
			OMM OMM Chip Breaker: Suitable for semi-finishing ISO M material.	General Chipbreaker: General Chip Breaker: Suitable for cast iron semi-finishing cutting.	NL NL Chip Breaker: Suitable for aluminum and aluminum alloy material.	OSM OSM Chip Breaker: Suitable for hi-temp alloy semi-finishing machining
Roughing	OPR OPR Chip Breaker: Suitable for roughing ISO P material.	OTR OTR Chip Breaker: Suitable for finishing ISO M material.		OKR Suitable for gray cast iron, nodular cast iron interrupt and roughing cutting at high feed, and high speed.		
				Flat: Flat Chip Breaker: Suitable for cast iron roughing cutting		

Grade Overview

ISO Usage	ISO Turning			Threading	Parting and Grooving			Milling			Drilling		
	Coating			Coating	Coating			Coating			Coating		
	CVD	PVD	Uncoated Carbide	PVD	CVD	PVD	Uncoated Carbide	CVD	PVD	Uncoated Carbide	CVD	PVD	
Steel	01			OP1210									
	10	OC2115				OP1215		OP1215	OP1215	OP1315	OP1325	OP1630	OP2202
	20	OC2125	OC2325										
	30	OC2125	OC2325	OC2325S									
	40			OC2425									
Stainless Steel	01	OC4315		OP1210									
	10		OP1215	OP1315								OP1215	
	20		OP1215	OP1315								OP1030	
	30												
	40												
Cast Iron	01												
	10		OC3215		OC4020								
	20	OC3210	OC3220										
	30												
	40												
Aluminum Alloy	01												
	10			OK434									
	20												
	30												
	40												
Hi-temp Alloy	01												
	10			OP1105									
	20			OP6115									
	30			OP6215									


Turning Insert (Negative) CN□□



Insert Shape	Type	Dimension					P		M		K		S										
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215		
	CNMG120404-OPF	12.9	12.7	4.76	5.16	0.4	●	●	▲														
	CNMG120408-OPF	12.9	12.7	4.76	5.16	0.8	●	●	▲														
	CNMG120404-OMF	12.9	12.7	4.76	5.16	0.4				●	●	▲											
	CNMG120408-OMF	12.9	12.7	4.76	5.16	0.8				●	●	▲											
	CNMG090304-MSF	9.7	9.525	3.18	3.81	0.4				●	●	▲											
	CNMG120404-MSF	12.9	12.7	4.76	5.16	0.4				●	●	▲											
	CNMG120404-OPM	12.9	12.7	4.76	5.16	0.4	●	●	▲														
	CNMG120408-OPM	12.9	12.7	4.76	5.16	0.8	●	●	▲														
	CNMG120412-OPM	12.9	12.7	4.76	5.16	1.2	●	●	▲														
	CNMG120416-OPM	12.9	12.7	4.76	5.16	1.6	●	●	▲														
	CNMG160608-OPM	16.1	15.875	6.35	6.35	0.8	●	●	▲														
	CNMG160612-OPM	16.1	15.875	6.35	6.35	1.2	●	●	▲														
	CNMG160616-OPM	16.1	15.875	6.35	6.35	1.6	●	●	▲														
	CNMG190608-OPM	19.3	19.05	6.35	7.94	0.8	●	●	▲	▲													
CNMG190612-OPM	19.3	19.05	6.35	7.94	1.2	●	●	▲	▲														
CNMG190616-OPM	19.3	19.05	6.35	7.94	1.6	●	●	▲	▲														

▲ Featured grade ● Optional grade


Turning Insert (Negative) CN□□



Insert Shape	Type	Dimension					P					M			K		S					
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	CNMG120404-OMM	12.9	12.7	4.76	5.16	0.4						●	▲	●								
	CNMG120408-OMM	12.9	12.7	4.76	5.16	0.8						●	▲	●								
	CNMG160608-OMM	16.1	15.875	6.35	6.35	0.8						●	▲	●								
	CNMG090308-MF	9.7	9.525	3.18	3.81	0.8						●	▲	●								
	CNMG120404-MF	12.9	12.7	4.76	5.16	0.4						●	▲	●								
	CNMG120408-MF	12.9	12.7	4.76	5.16	0.8						●	▲	●								
	CNMG120412-MF	12.9	12.7	4.76	5.16	1.2						●	▲	●								
	CNMG160612-MF	16.1	15.875	6.35	6.35	1.6						●	▲	●								
	CNMG120404-OKM	12.9	12.7	4.76	5.16	0.4									▲	▲						
	CNMG120408-OKM	12.9	12.7	4.76	5.16	0.8									▲	▲						
	CNMG120412-OKM	12.9	12.7	4.76	5.16	1.2									▲	▲						
	CNMG120408-OSM	12.9	12.7	4.76	5.16	0.8														●		
	CNMG120412-OSM	12.9	12.7	4.76	5.16	1.2														●		
	CNMG120408-SMM	12.9	12.7	4.76	5.16	0.8														▲	▲	
	CNMG120404-SMM	12.9	12.7	4.76	5.16	0.4														▲	▲	

Semi Finishing

Turning Insert (Negative) CN□□




Insert Shape	Type	Dimension					P					M			K		S					
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	CNMG120408-OPR	12.9	12.7	4.76	5.16	0.8	●	●	▲													
	CNMG120412-OPR	12.9	12.7	4.76	5.16	1.2	●	●	▲													
	CNMG120416-OPR	12.9	12.7	4.76	5.16	1.6	●	●	▲													
	CNMG160608-OPR	16.1	15.875	6.35	6.35	0.8	●	●	▲													
	CNMG160612-OPR	16.1	15.875	6.35	6.35	1.2	●	●	▲													
	CNMG160616-OPR	16.1	15.875	6.35	6.35	1.6	●	●	▲													
	CNMG190608-OPR	19.3	19.05	6.35	7.94	0.8	●	●	▲	▲												
	CNMG190612-OPR	19.3	19.05	6.35	7.94	1.2	●	●	▲	▲												
	CNMG190616-OPR	19.3	19.05	6.35	7.94	1.6	●	●	▲	▲												
	CNMG120408-OMR	12.9	12.7	4.76	5.16	0.8						●	▲	●								
	CNMG120412-OMR	12.9	12.7	4.76	5.16	1.2						●	▲	●								
	CNMG120408-OKR	12.9	12.7	4.76	5.16	0.8														▲	▲	
	CNMG120412-OKR	12.9	12.7	4.76	5.16	1.2														▲	▲	
	CNMG120416-OKR	12.9	12.7	4.76	5.16	1.6														▲	▲	
	CNMG160612-OKR	16.1	15.8	6.35	6.35	1.2														▲	▲	
	CNMM190616-PR	19.3	19.05	6.35	7.94	1.6	●	●	▲													
	CNMM250924-PR	25.8	25.4	9.72	9.12	2.4								▲								
	CNMM250724-PR	25.8	25.4	7.94	9.12	2.4								▲								

Roughing

Heavy Duty Machining


▲ Featured grade ● Optional grade

Turning Insert (Negative) CN□□




Insert Shape	Type	Dimension					P				M				K		S					
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	CNMG120404	12.9	12.7	4.76	5.16	0.4	●	●	▲							▲						
	CNMG120408	12.9	12.7	4.76	5.16	0.8	●	●	▲							▲						
	CNMG120412	12.9	12.7	4.76	5.16	1.2	●	●	▲							▲						
	CNMG160608	16.1	15.875	6.35	6.35	0.8	●	●	▲							▲						
	CNMG160612	16.1	15.875	6.35	6.35	1.2	●	●	▲							▲						
	CNMG160616	16.1	15.875	6.35	6.35	1.6	●	●	▲							▲						
	CNMG190608	19.3	19.05	6.35	7.94	0.8	●	●	▲							▲						
	CNMG190612	19.3	19.05	6.35	7.94	1.2	●	●	▲							▲						
	CNMG190616	19.3	19.05	6.35	7.94	1.6	●	●	▲							▲						
	CNMA120404	12.9	12.7	4.76	5.16	0.4										▲						
	CNMA120408	12.9	12.7	4.76	5.16	0.8										▲						
	CNMA120412	12.9	12.7	4.76	5.16	1.2										▲						
	CNMA120416	12.9	12.7	4.76	5.16	1.6										▲						
	CNMA160608	16.1	15.875	6.35	6.35	0.8										▲						
	CNMA160612	16.1	15.875	6.35	6.35	1.2										▲						
	CNMA160616	16.1	15.875	6.35	6.35	1.6										▲						
	CNMA190612	19.3	19.05	6.35	7.94	1.2										▲						
	CNMA190616	19.3	19.05	6.35	7.94	1.6										▲						

Turning Insert (Negative) DN□□




Insert Shape	Type	Dimension					P				M				K		S					
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	DNMG110404-OPF	11.6	9.525	4.76	3.81	0.4	●	●	▲													
	DNMG110408-OPF	11.6	9.525	4.76	3.81	0.8	●	●	▲													
	DNMG150404-OPF	15.5	12.7	4.76	5.16	0.4	●	●	▲													
	DNMG150408-OPF	15.5	12.7	4.76	5.16	0.8	●	●	▲													
	DNMG150604-OPF	15.5	12.7	6.35	5.16	0.4	●	●	▲													
	DNMG150608-OPF	15.5	12.7	6.35	5.16	0.8	●	●	▲													
	DNMG150604-OMF	15.5	12.7	6.35	5.16	0.4						●	▲	●								
	DNMG150608-OMF	15.5	12.7	6.35	5.16	0.8						●	▲	●								
	DNMG110404-MSF	11.6	9.525	4.76	3.81	0.4						●	▲	●								
	DNMG150404-MSF	15.5	12.7	4.76	5.16	0.4						●	▲	●								
	DNMG110404-OPM	11.6	9.525	4.76	3.81	0.4	●		▲													
	DNMG110408-OPM	11.6	9.525	4.76	3.81	0.8	●		▲													
	DNMG110412-OPM	11.6	9.525	4.76	3.81	1.2	●		▲													
	DNMG150404-OPM	15.5	12.7	4.76	5.16	0.4	●		▲													
	DNMG150408-OPM	15.5	12.7	4.76	5.16	0.8	●		▲													
	DNMG150412-OPM	15.5	12.7	4.76	5.16	1.2	●		▲													
	DNMG150604-OPM	15.5	12.7	6.35	5.16	0.4	●		▲													
	DNMG150608-OPM	15.5	12.7	6.35	5.16	0.8	●		▲													
DNMG150612-OPM	15.5	12.7	6.35	5.16	1.2	●		▲														
	DNMG110404-OMM	11.6	9.525	4.76	3.81	0.4						●	▲	●								
	DNMG110408-OMM	11.6	9.525	4.76	3.81	0.8						●	▲	●								
	DNMG150404-OMM	15.5	12.7	4.76	5.16	0.4						●	▲	●								
	DNMG150408-OMM	15.5	12.7	4.76	5.16	0.8						●	▲	●								
	DNMG150604-OMM	15.5	12.7	6.35	5.16	0.4						●	▲	●								
	DNMG150608-OMM	15.5	12.7	6.35	5.16	0.8						●	▲	●								
	DNMG150612-OMM	15.5	12.7	6.35	5.16	1.2						●	▲	●								
	DNMG110408-MF	11.6	9.525	4.76	3.81	0.8						●	▲	●								
DNMG150408-MF	15.5	12.7	4.76	5.16	0.8						●	▲	●									
DNMG150608-MF	15.5	12.7	6.35	5.16	0.8						●	▲	●									

Turning Insert (Negative) DN□□



Insert Shape	Type	Dimension					P					M				K			S			
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	DNMG150404-OKM	15.5	12.7	4.76	5.16	0.4												▲	▲			
	DNMG150408-OKM	15.5	12.7	4.76	5.16	0.8												▲	▲			
	DNMG150604-OKM	15.5	12.7	6.35	5.16	0.4												▲	▲			
	DNMG150608-OKM	15.5	12.7	6.35	5.16	0.8												▲	▲			
	DNMG150612-OKM	15.5	12.7	6.35	5.16	1.2												▲	▲			
	DNMG150608-OSM	15.5	12.7	6.35	5.16	0.8														●		
	DNMG150408-OPR	15.5	12.7	4.76	5.16	0.8	●	●	▲													
	DNMG150412-OPR	15.5	12.7	4.76	5.16	1.2	●	●	▲													
	DNMG150608-OPR	15.5	12.7	6.35	5.16	0.8	●	●	▲													
	DNMG150612-OPR	15.5	12.7	6.35	5.16	1.2	●	●	▲													
	DNMG150616-OPR	15.5	12.7	6.35	5.16	1.6	●	●	▲													
		DNMG150408-OKR	15.5	12.7	4.76	5.16	0.8											▲	▲			
DNMG150412-OKR		15.5	12.7	4.76	5.16	1.2											▲	▲				
DNMG150608-OKR		15.5	12.7	6.35	5.16	0.8											▲	▲				
DNMG150612-OKR		15.5	12.7	6.35	5.16	1.2											▲	▲				
	DNMG110408	11.6	9.525	4.76	3.81	0.8	●	●	▲									▲				
	DNMG150404	15.5	12.7	4.76	5.16	0.4	●	●	▲									▲				
	DNMG150408	15.5	12.7	6.35	5.16	0.8	●	●	▲									▲				
	DNMG150412	15.5	12.7	6.35	5.16	1.2	●	●	▲									▲				
	DNMG150608	15.5	12.7	6.35	5.16	0.8	●	●	▲									▲				
	DNMG150612	15.5	12.7	6.35	5.16	1.2	●	●	▲									▲				
	DNMA150404	15.5	12.7	4.76	5.16	0.4												▲				
	DNMA150408	15.5	12.7	4.76	5.16	0.8												▲				
	DNMA150604	15.5	12.7	6.35	5.16	0.4												▲				
	DNMA150608	15.5	12.7	6.35	5.16	0.8												▲				
	DNMA150612	15.5	12.7	6.35	5.16	1.2												▲				


Turning Insert (Negative) SN□□



Insert Shape	Type	Dimension					P					M				K			S			
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	SNMG120404-OPF	12.7	12.7	4.76	5.16	0.4	●	●	▲													
	SNMG120408-OPF	12.7	12.7	4.76	5.16	0.8	●	●	▲													
	SNMG120408-OMF	12.7	12.7	4.76	5.16	0.8												●	▲	●		
	SNMG120404-OPM	12.7	12.7	4.76	5.16	0.4	●		▲													
	SNMG120408-OPM	12.7	12.7	4.76	5.16	0.8	●		▲													
	SNMG120412-OPM	12.7	12.7	4.76	5.16	1.2	●		▲													
	SNMG150608-OPM	15.875	15.875	6.35	6.35	0.8	●		▲													
	SNMG150612-OPM	15.875	15.875	6.35	6.35	1.2	●		▲													
	SNMG190612-OPM	19.05	19.05	6.35	7.94	1.2	●		▲													
	SNMG120404-OMM	12.7	12.7	4.76	5.16	0.4												●	▲	●		
	SNMG120408-OMM	12.7	12.7	4.76	5.16	0.8												●	▲	●		
	SNMG120412-OMM	12.7	12.7	4.76	5.16	1.2												●	▲	●		
	SNMG150608-OMM	15.875	15.875	6.35	6.35	0.8												●	▲	●		
	SNMG120408-MF	12.7	12.7	4.76	5.16	0.8												●	▲	●		


▲ Featured grade ● Optional grade

Turning Insert (Negative) SN□□



Insert Shape	Type	Dimension					P					M			K		S						
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215		
	SNMG120404-OKM	12.7	12.7	4.76	5.16	0.4											▲	▲					
	SNMG120408-OKM	12.7	12.7	4.76	5.16	0.8											▲	▲					
	SNMG120412-OKM	12.7	12.7	4.76	5.16	1.2											▲	▲					
	SNMG120408-OSM	12.7	12.7	4.76	5.16	0.8															●		
	SNMG120408-SMM	12.7	12.7	4.76	5.16	0.8											▲	▲					
	SNMG120408-OPR	12.7	12.7	4.76	5.16	0.8	●	●	▲														
	SNMG120412-OPR	12.7	12.7	4.76	5.16	1.2	●	●	▲														
	SNMG150608-OPR	15.875	15.875	6.35	6.35	0.8	●	●	▲														
	SNMG150612-OPR	15.875	15.875	6.35	6.35	1.2	●	●	▲														
	SNMG150616-OPR	15.875	15.875	6.35	6.35	1.6	●	●	▲														
	SNMG190612-OPR	19.05	19.05	6.35	7.94	1.2	●	●	▲														
	SNMG190616-OPR	19.05	19.05	6.35	7.94	1.6	●	●	▲														
	SNMM190624-OPR	19.05	19.05	6.35	7.94	2.4	●	●	▲														
	SNMG120408-OKR	12.7	12.7	4.76	5.16	0.8											▲	▲					
	SNMG120412-OKR	12.7	12.7	4.76	5.16	1.2											▲	▲					
	SNMG120416-OKR	12.7	12.7	4.76	5.16	1.6											▲	▲					
	SNMG150616-OKR	15.875	15.875	6.35	6.35	1.6											▲	▲					
	SNMG190612-OKR	19.05	19.05	6.35	7.94	1.2											▲	▲					


Turning Insert (Negative) SN□□



Insert Shape	Type	Dimension					P					M			K		S					
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	SNMM250724-PR	25.4	25.4	9.525	9.12	2.4					▲											
	SNMM250924-PR	25.4	25.4	9.525	9.12	2.4					▲											
	SNMG120404	12.7	12.7	4.76	5.16	0.4	●	●	▲									▲				
	SNMG120408	12.7	12.7	4.76	5.16	0.8	●	●	▲									▲				
	SNMG120412	12.7	12.7	4.76	5.16	1.2	●	●	▲									▲				
	SNMG120416	12.7	12.7	4.76	5.16	1.6	●	●	▲									▲				
	SNMG150608	15.875	15.875	6.35	6.35	0.8	●	●	▲									▲				
	SNMG150612	15.875	15.875	6.35	6.35	1.2	●	●	▲									▲				
	SNMG190612	19.05	19.05	6.35	7.94	1.2	●	●	▲									▲				
	SNMG190616	19.05	19.05	6.35	7.94	1.6	●	●	▲									▲				
	SNMG250724	25.4	25.4	7.94	9.12	2.4	●	●	▲									▲				
	SNMG250924	25.4	25.4	9.525	9.12	2.4	●	●	▲									▲				
	SNMA120408	12.7	12.7	4.76	5.16	0.8												▲				
	SNMA120412	12.7	12.7	4.76	5.16	1.2												▲				
	SNMA120416	12.7	12.7	4.76	5.16	1.6												▲				

▲ 主推牌号 ● 可选牌号 ▲ Featured grade ● Optional grade


Turning Insert (Negative) TN□□



Insert Shape	Type	Dimension					P					M			K		S					
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	TNMG160404-OPF	16.5	9.525	4.76	3.81	0.4	●	●	▲													
	TNMG160408-OPF	16.5	9.525	4.76	3.81	0.8	●	●	▲													
	TNMG160404-OMF	16.5	9.525	4.76	3.81	0.4					●	▲	●									
	TNMG160408-OMF	16.5	9.525	4.76	3.81	0.8					●	▲	●									
	TNMG160404-MSF	16.5	9.525	4.76	3.81	0.4					●	▲	●									
	TNMG160408-MSF	16.5	9.525	4.76	3.81	0.8					●	▲	●									

Finishing

Turning Insert (Negative) TN□□




Insert Shape	Type	Dimension					P					M			K		S					
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	TNMG160404-OPM	16.5	9.525	4.76	3.81	0.4	●		▲													
	TNMG160408-OPM	16.5	9.525	4.76	3.81	0.8	●		▲													
	TNMG160412-OPM	16.5	9.525	4.76	3.81	1.2	●		▲													
	TNMG220404-OPM	22	12.7	4.76	5.16	0.4	●		▲													
	TNMG220408-OPM	22	12.7	4.76	5.16	0.8	●		▲													
	TNMG220412-OPM	22	12.7	4.76	5.16	1.2	●		▲													
	TNMG220416-OPM	22	12.7	4.76	5.16	1.6	●		▲													
	TNMG160404-OMM	16.5	9.525	4.76	3.81	0.4					●	▲	●									
	TNMG160408-OMM	16.5	9.525	4.76	3.81	0.8					●	▲	●									
	TNMG220404-OMM	22	12.7	4.76	5.16	0.4					●	▲	●									
	TNMG220408-OMM	22	12.7	4.76	5.16	0.8					●	▲	●									
	TNMG220412-OMM	22	12.7	4.76	5.16	1.2					●	▲	●									
	TNMG160404-MF	16.5	9.525	4.76	3.81	0.4					●	▲	●									
	TNMG160408-MF	16.5	9.525	4.76	3.81	0.8					●	▲	●									
	TNMG160412-MF	16.5	9.525	4.76	3.81	1.2					●	▲	●									
	TNMG220404-MF	22	12.7	4.76	5.16	0.4					●	▲	●									
	TNMG220408-MF	22	12.7	4.76	5.16	0.8					●	▲	●									
	TNMG220412-MF	22	12.7	4.76	5.16	1.2					●	▲	●									
	TNMG160404-OKM	16.5	9.525	4.76	3.81	0.4												▲	▲			
	TNMG160408-OKM	16.5	9.525	4.76	3.81	0.8												▲	▲			
	TNMG160412-OKM	16.5	9.525	4.76	3.81	1.2												▲	▲			
	TNMG160408-SMM	16.5	9.525	4.76	3.81	0.8															▲	▲

Semi Finishing


▲Featured grade ●Optional grade

Turning Insert (Negative) TN□□



Insert Shape	Type	Dimension					P					M			K		S					
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	TNMG160408-OPR	16.5	9.525	4.76	3.81	0.8	●	●	▲													
	TNMG160412-OPR	16.5	9.525	4.76	3.81	1.2	●	●	▲													
	TNMG220408-OPR	22	12.7	4.76	5.16	0.8	●	●	▲													
	TNMG220412-OPR	22	12.7	4.76	5.16	1.2	●	●	▲													
	TNMG220416-OPR	22	12.7	4.76	5.16	1.6	●	●	▲													
	TNMG270612-OPR	27.5	15.875	6.35	6.35	1.2	●	●	▲													
	TNMG160408-OMR	16.5	9.525	4.76	3.81	0.8					●	▲	●									
	TNMG160408-OKR	16.5	9.525	4.76	3.81	0.8									▲	▲						
	TNMG160412-OKR	16.5	9.525	4.76	3.81	1.2									▲	▲						


Turning Insert (Negative) TN□□



Insert Shape	Type	Dimension					P					M			K		S					
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	TNMG160404	16.5	9.525	4.76	3.81	0.8	●	●	▲										▲			
	TNMG160408	16.5	9.525	4.76	3.81	1.2	●	●	▲										▲			
	TNMG160412	22	12.7	4.76	5.16	0.4	●	●	▲										▲			
	TNMG220408	22	12.7	4.76	5.16	0.8	●	●	▲										▲			
	TNMG220412	22	12.7	4.76	5.16	1.2	●	●	▲										▲			
	TNMG220416	22	12.7	4.76	5.16	1.6	●	●	▲										▲			
	TNMA160404	16.5	9.525	4.76	3.81	0.4													▲			
	TNMA160408	16.5	9.525	4.76	3.81	0.8													▲			
	TNMA160412	16.5	9.525	4.76	3.81	1.2													▲			
	TNMA220408	22	12.7	4.76	5.16	0.8													▲			
	TNMA220412	22	12.7	4.76	5.16	1.2													▲			


▲ Featured grade ● Optional grade

Turning Insert (Negative) VN□□



Insert Shape	Type	Dimension					P					M			K		S					
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	VNMG160404-OPF	16.6	9.525	4.76	3.81	0.4	●	●	▲													
	VNMG160408-OPF	16.6	9.525	4.76	3.81	0.8	●	●	▲													
	VNMG160404-MSF	16.6	9.525	4.76	3.81	0.4					●	▲	●									
	VNMG160404-OPM	16.6	9.525	4.76	3.81	0.4	●		▲													
	VNMG160408-OPM	16.6	9.525	4.76	3.81	0.8	●		▲													
	VNMG160412-OPM	16.6	9.525	4.76	3.81	1.2	●		▲													
	VNMG160404-OMM	16.6	9.525	4.76	3.81	0.4					●	▲	●									
	VNMG160408-OMM	16.6	9.525	4.76	3.81	0.8					●	▲	●									
	VNMG160408-MF	16.6	9.525	4.76	3.81	0.8					●	▲	●									


Turning Insert (Negative) VN□□



Insert Shape	Type	Dimension					P					M			K		S						
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215		
	VNMG160404-OKM	16.6	9.525	4.76	3.81	0.4														▲	▲		
	VNMG160408-OKM																				▲	▲	
	VNMG160408-SMM	16.6	9.525	4.76	3.81	0.8																▲	▲


▲ Featured grade ● Optional grade

Turning Insert (Negative) VN□□



Insert Shape	Type	Dimension					P					M			K		S					
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	VNMG160408-OPR	16.6	9.525	4.76	3.81	0.4	●	●	▲													
	VNMG160412-OPR	16.6	9.525	4.76	3.81	0.8	●	●	▲													
	VNMG160408-OKR	16.6	9.525	4.76	3.81	0.4									▲		▲					
	VNMG160412-OKR	16.6	9.525	4.76	3.81	0.8									▲		▲					
	VNMG160404	16.6	9.525	4.76	3.81	0.4	●	●	▲								▲					
	VNMG160408	16.6	9.525	4.76	3.81	0.8	●	●	▲								▲					
	VNMG160412	16.6	9.525	4.76	3.81	1.2	●	●	▲								▲					
	VNMA160408	16.6	9.525	4.76	3.81	0.8											▲					


Turning Insert (Negative) WN□□



Insert Shape	Type	Dimension					P					M			K		S					
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	WNMG060404-OPF	6.5	9.525	4.76	3.81	0.4	●	●	▲													
	WNMG060408-OPF	6.5	9.525	4.76	3.81	0.8	●	●	▲													
	WNMG060408-OMF	6.5	9.525	4.76	3.81	0.8						●	▲	●								
	WNMG080404-OMF	8.7	12.7	4.76	5.16	0.4						●	▲	●								
	WNMG080408-OMF	8.7	12.7	4.76	5.16	0.8						●	▲	●								
	WNMG060304-MSF	6.5	9.525	3.18	3.81	0.4						●	▲	●								
	WNMG060404-MSF	6.5	9.525	4.76	3.81	0.4						●	▲	●								
	WNMG080404-MSF	8.7	12.7	4.76	5.16	0.4						●	▲	●								
	WNMG060408-OPM	6.5	9.525	4.76	3.81	0.8	●		▲													
	WNMG080404-OPM	8.7	12.7	4.76	5.16	0.4	●		▲													
	WNMG080408-OPM	8.7	12.7	4.76	5.16	0.8	●		▲													
	WNMG080412-OPM	8.7	12.7	4.76	5.16	1.2	●		▲													
	WNMG060408-OMM	6.5	9.525	4.76	3.81	0.8						●	▲	●								
	WNMG060412-OMM	6.5	9.525	4.76	3.81	1.2						●	▲	●								
	WNMG080404-OMM	8.7	12.7	4.76	5.16	0.4						●	▲	●								
	WNMG080408-OMM	8.7	12.7	4.76	5.16	0.8						●	▲	●								
	WNMG060408-MF	6.5	9.525	4.76	3.81	0.8						●	▲	●								
	WNMG080408-MF	8.7	12.7	4.76	5.16	0.8						●	▲	●								
	WNMG080412-MF	8.7	12.7	4.76	5.16	1.2						●	▲	●								


▲Featured grade ●Optional grade

Turning Insert (Negative) WN□□



Insert Shape	Type	Dimension					P					M			K		S					
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	WNMG080404-OKM	8.7	12.7	4.76	5.16	0.4										▲	▲					
	WNMG080408-OKM	8.7	12.7	4.76	5.16	0.8										▲	▲					
	WNMG080412-OKM	8.7	12.7	4.76	5.16	1.2										▲	▲					
	WNMG080408-SMM	8.7	12.7	4.76	5.16	0.8												▲			▲	
	WNMG080408-OPR	8.7	12.7	4.76	5.16	0.8	●	●	▲													
	WNMG080412-OPR	8.7	12.7	4.76	5.16	1.2	●	●	▲													
	WNMG080408-OMR	8.7	12.7	4.76	5.16	0.8					●	▲	●									
	WNMG080412-OMR	8.7	12.7	4.76	5.16	1.2					●	▲	●									
	WNMG080408-OKR	8.7	12.7	4.76	5.16	0.8									▲	▲						
	WNMG080412-OKR	8.7	12.7	4.76	5.16	1.2									▲	▲						
	WNMG080404	8.7	12.7	4.76	5.16	0.4	●	●	▲							▲						
	WNMG080408	8.7	12.7	4.76	5.16	0.8	●	●	▲							▲						
	WNMG080412	8.7	12.7	4.76	5.16	1.2	●	●	▲							▲						
	WNMA080408	8.7	12.7	4.76	5.16	0.8										▲						
	WNMA080412	8.7	12.7	4.76	5.16	1.2										▲						


Turning Insert (Positive) CC□□



Insert Shape	Type	Dimension					P					M			K		S					
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	CCMT060202-OTF	6.4	6.35	2.38	2.8	0.2	▲					●	▲	●								
	CCMT060204-OTF	6.4	6.35	2.38	2.8	0.4	▲					●	▲	●								
	CCMT09T304-OTF	9.7	9.525	3.97	4.4	0.4	▲					●	▲	●								
	CCMT09T308-OTF	9.7	9.525	3.97	4.4	0.8	▲					●	▲	●								
	CCMT120404-OTF	12.9	12.7	4.76	5.5	0.4	▲					●	▲	●								
	CCMT120408-OTF	12.9	12.7	4.76	5.5	0.8	▲					●	▲	●								
	CCMT060202-MSF	6.4	6.35	2.38	2.8	0.2						●	▲	●								
	CCMT060204-MSF	6.4	6.35	2.38	2.8	0.4						●	▲	●								
	CCMT09T302-MSF	9.7	9.525	3.97	4.4	0.2						●	▲	●								
	CCMT09T304-MSF	9.7	9.525	3.97	4.4	0.4						●	▲	●								
	CCMT09T308-MSF	12.9	12.7	4.76	5.5	0.8						●	▲	●								
	CCMT120404-MSF	12.9	12.7	4.76	5.5	0.4						●	▲	●								
	CCMT060204-OTM	6.4	6.35	2.38	2.8	0.4	●	●	▲			●	▲	●								
	CCMT060208-OTM	6.4	6.35	2.38	2.8	0.8	●	●	▲			●	▲	●								
	CCMT09T304-OTM	9.7	9.525	3.97	4.4	0.4	●	●	▲			●	▲	●								
	CCMT09T308-OTM	9.7	9.525	3.97	4.4	0.8	●	●	▲			●	▲	●								
	CCMT120404-OTM	12.9	12.7	4.76	5.5	0.4	●	●	▲			●	▲	●								
	CCMT120408-OTM	12.9	12.7	4.76	5.5	0.8	●	●	▲			●	▲	●								
	CCMT060208-OTR	6.4	6.35	2.38	2.8	0.8	●	●	▲									▲				
	CCMT09T304-OTR	9.7	9.525	3.97	4.4	0.4	●	●	▲									▲				
	CCMT09T308-OTR	9.7	9.525	3.97	4.4	0.8	●	●	▲									▲				
	CCMT120408-OTR	12.9	12.7	4.76	5.5	0.8	●	●	▲									▲				


▲Featured grade ●Optional grade

Turning Insert (Positive) DC□□



Insert Shape	Type	Dimension					P					M			K		S						
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215		
	DCMT070204-OTF	7.8	6.35	2.38	2.8	0.4	▲					●	▲	●									
	DCMT11T302-OTF	11.6	9.525	3.97	4.4	0.2	▲					●	▲	●									
	DCMT11T304-OTF	11.6	9.525	3.97	4.4	0.4	▲					●	▲	●									
	DCMT070204-MSF	7.8	6.35	2.38	2.8	0.4						●	▲	●									
	DCMT11T304-MSF	11.6	9.525	3.97	4.4	0.4						●	▲	●									
	DCMT070204-OTM	7.8	6.35	2.38	2.8	0.4	●	●	●	▲		●	▲	●									
	DCMT070208-OTM	7.8	6.35	2.38	2.8	0.8	●	●	●	▲		●	▲	●									
	DCMT11T304-OTM	11.6	9.525	3.97	4.4	0.4	●	●	●	▲		●	▲	●									
	DCMT11T308-OTM	11.6	9.525	3.97	4.4	0.8	●	●	●			●	▲	●									
	DCMT11T304-OTR	11.6	9.525	3.97	4.4	0.4	●	●	●	▲		●	▲	●									
	DCMT11T308-OTR	11.6	9.525	3.97	4.4	0.8	●	●	●	▲		●	▲	●									


Turning Insert (Positive) RC□□



Insert Shape	Type	Dimension					P					M			K		S						
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215		
	RCMX0803MO	8.0	8.0	3.18	3.4		▲	●															
	RCMX1003MO	10	10	3.18	3.6		▲	●															
	RCMX1204MO-Q	12	12	4.76	4.4		▲	●															
	RCMX1606MO-Q	16	16	6.35	5.5		▲	●															
	RCMX2006MO-Q	20	20	6.35	6.5		▲	●															
	RCMX2507MO-Q	25	25	7.94	7.2		▲	●															
	RCMX3209MO-Q	32	32	9.52	9.5		▲	●															
	RCMT0803MO	8.0	8.0	3.18	3.4		▲	●															
	RCMT1606MO-Q	16	16	6.35	5.5		▲	●															


▲ Featured grade ● Optional grade

Turning Insert (Positive) SC□□



Insert Shape	Type	Dimension					P					M			K		S					
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	Finishing																					
	SCMT09T304-OTF	9.525	9.525	3.97	4.4	0.4	●				●	▲	●									
	SCMT09T308-OTF	9.525	9.525	3.97	4.4	0.8	●				●	▲	●									
SCMT120404-OTF	12.7	12.7	4.76	5.5	0.4	●				●	▲	●										
	Semi Finishing																					
	SCMT09T304-OTM	9.525	9.525	3.97	4.4	0.4	●	●	●	▲	●	▲	●									
	SCMT09T308-OTM	9.525	9.525	3.97	4.4	0.8	●	●	●	▲	●	▲	●									
	SCMT120404-OTM	12.7	12.7	4.76	5.5	0.4	●	●	●	▲	●	▲	●									
	SCMT120408-OTM	12.7	12.7	4.76	5.5	0.8	●	●	●	▲	●	▲	●									
SCMT120412-OTM	12.7	12.7	4.76	5.5	1.2	●	●	●	▲	●	▲	●										
	Roughing																					
	SCMT09T304-OTR	9.525	9.525	3.97	4.4	0.4	●	●	●	▲							▲					
	SCMT09T308-OTR	9.525	9.525	3.97	4.4	0.8	●	●	●	▲							▲					
	SCMT120404-OTR	12.7	12.7	4.76	5.5	0.4	●	●	●	▲							▲					
	SCMT120408-OTR	12.7	12.7	4.76	5.5	0.8	●	●	●	▲							▲					
SCMT120412-OTR	12.7	12.7	4.76	5.5	1.2	●	●	●	▲							▲						


Turning Insert (Positive) TC□□



Insert Shape	Type	Dimension					P					M			K		S					
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	Finishing																					
	TCMT110202-OTF	11	6.35	2.38	2.8	0.2	▲					●	▲	●								
	TCMT110204-OTF	11	6.35	2.38	2.8	0.4	▲					●	▲	●								
	TCMT16T304-OTF	16.5	9.525	3.97	4.4	0.4	▲					●	▲	●								
	TCMT16T308-OTF	16.5	9.525	3.97	4.4	0.8	▲					●	▲	●								
	Semi Finishing																					
	TCMT090204-OTM	9.6	5.56	2.38	2.5	0.4	●	●	●	▲	●	▲	●									
	TCMT090208-OTM	9.6	5.56	2.38	2.5	0.8	●	●	●	▲	●	▲	●									
	TCMT110204-OTM	11	6.35	2.38	2.8	0.4	●	●	●	▲	●	▲	●									
	TCMT110208-OTM	11	6.35	2.38	2.8	0.8	●	●	●	▲	●	▲	●									
	TCMT16T304-OTM	16.5	9.525	3.97	4.4	0.4	●	●	●	▲	●	▲	●									
	TCMT16T308-OTM	16.5	9.525	3.97	4.4	0.8	●	●	●	▲	●	▲	●									
TCMT16T312-OTM	16.5	9.525	3.97	4.4	1.2	●	●	●	▲	●	▲	●										
	Roughing																					
	TCMT16T308-OTR	16.5	9.525	3.97	4.4	0.8	●	●	●	▲								▲				
	TCMT220408-OTR	22	12.7	4.76	5.5	0.8	●	●	●	▲								▲				


▲ Featured grade ● Optional grade

Turning Insert (Positive) VB□□



Insert Shape	Type	Dimension					P					M			K		S					
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	VBMT160404-OTF	16.5	9.525	4.76	4.4	0.4	▲					●	▲	●								
	VBMT160408-OTF	16.5	9.525	4.76	4.4	0.8	▲					●	▲	●								
	VBMT110304-OTM	11	6.35	3.18	2.8	0.4	●	●	●	▲		●	▲	●								
	VBMT160404-OTM	16.5	9.525	4.76	4.4	0.4	●	●	●	▲		●	▲	●								
	VBMT160408-OTM	16.5	9.525	4.76	4.4	0.8	●	●	●	▲		●	▲	●								
	VBMT160412-OTM	16.5	9.525	4.76	4.4	1.2	●	●	●	▲		●	▲	●								
	VBMT160404-OMM	16.5	9.525	4.76	4.4	0.4						●	▲	●								
	VBMT160404-OSM	16.5	9.525	4.76	4.4	0.4													●	▲	▲	
	VBMT160408-OSM	16.5	9.525	4.76	4.4	0.8													●	▲	▲	
	VBMT160404-OTR	16.5	9.525	4.76	4.4	0.4	●	●	●	▲						▲						
	VBMT160408-OTR	16.5	9.525	4.76	4.4	0.8	●	●	●	▲						▲						


Turning Insert (Positive) VC□□




Insert Shape	Type	Dimension					P					M			K		S					
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	VCMT110302-OTF	11	6.35	3.18	2.8	0.2	▲					●	▲	●								
	VCMT110304-OTF	11	6.35	3.18	2.8	0.4	▲					●	▲	●								
	VCMT160404-OTF	16.5	9.525	4.76	4.4	0.4	▲					●	▲	●								
	VCMT160404-OTM	16.5	9.525	4.76	4.4	0.4	▲					●	▲	●								
	VCMT160408-OTM	16.5	9.525	4.76	4.4	0.8	▲					●	▲	●								
	VCMT160408-OSM	16.5	9.525	4.76	4.4	0.8														●	▲	▲


▲Featured grade ●Optional grade


Turning Insert (Positive) TB□□ TP□□



Insert Shape	Type	Dimension					P					M			K		S						
		LE	IC	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1205H	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	TBGH060202L	6.4	3.97	2.38	2.3	0.2						▲											
	TPGH080202L	8.2	4.76	2.38	2.4	0.2						▲											
	TPGH080204L	8.2	4.76	2.38	2.4	0.4						▲											
	TPGH090202L	9.6	5.56	2.38	2.8	0.2						▲											
	TPGH090204L	9.6	5.56	2.38	2.8	0.4						▲											
	TPGH110302L	11	6.35	3.18	3.18	0.2						▲											
	TPGH110304L	11	6.35	3.18	3.18	0.4						▲											


Turning Insert (Positive) KN□□



Insert Shape	Type	Dimension					P					M			K		S					
		LE	W1	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220	OP1105	OP6115	OP6215	
	KNUX160405L11	16.2	9.525	4.76	2.2	0.5		▲	●													
	KNUX160405R11	16.2	9.525	4.76	2.2	0.5		▲	●													

▲Featured grade ●Optional grade


Train Wheel Hub Machining



Insert Shape	Type	Dimension					P					M				K		
		LE	W1	S	D1	RE	OC2115	OC2125	OC2325	OC2325S	OC2425	OP1215	OP1315	OP1415	OC4315	OC3210	OC3215	OC3220
	175.32-191940-22	19.1	10	19.1	6.35	4.0				▲								
	175.32-191940-28	19.1	10	19.1	6.35	4.0				▲								

Heavy Duty Machining

Insert for Aluminum Cutting CC□□ DC□□ RC□□




Insert Shape	Type	Dimension					N
		LE	IC	S	D1	RE	
	CCGX060202-NL	6.4	6.35	2.38	2.8	0.2	▲
	CCGX060204-NL	6.4	6.35	2.38	2.8	0.4	▲
	CCGX09T302-NL	9.7	9.525	3.97	4.4	0.2	▲
	CCGX09T304-NL	9.7	9.525	3.97	4.4	0.4	▲
	CCGX09T308-NL	9.7	9.525	3.97	4.4	0.8	▲
	CCGX120404-NL	12.9	12.7	4.76	5.5	0.4	▲
	CCGX120408-NL	12.9	12.7	4.76	5.5	0.8	▲
	DCGX070202-NL	7.8	6.35	2.38	2.8	0.2	▲
	DCGX070204-NL	7.8	6.35	2.38	2.8	0.4	▲
	DCGX11T302-NL	11.6	9.525	3.97	4.4	0.2	▲
	DCGX11T304-NL	11.6	9.525	3.97	4.4	0.4	▲
	DCGX11T308-NL	11.6	9.525	3.97	4.4	0.8	▲
	RCGT1204MO-NL	12	12	4.76	4.4	/	▲

▲Featured grade ●Optional grade


Insert for Aluminum Cutting

SC□□ TC□□ VC□□



Insert Shape	Type	Dimension					N	
		LE	IC	S	D1	RE		OK434
	SCGX09T304-NL	9.525	9.525	3.97	4.4	0.4	▲	
	SCGX09T308-NL	9.525	9.525	3.97	4.4	0.8	▲	
	SCGX120408-NL	12.7	12.7	4.76	5.5	0.8	▲	
	Finishing	TCGX090204-NL	9.6	5.56	2.38	2.5	0.4	▲
		TCGX110202-NL	11	6.35	2.38	2.8	0.2	▲
		TCGX110204-NL	11	6.35	2.38	2.8	0.4	▲
		TCGX16T304-NL	16.5	9.525	3.97	4.4	0.4	▲
		TCGX16T308-NL	16.5	9.525	3.97	4.4	0.8	▲
	VCGX110302-NL	11	6.35	3.18	2.8	0.2	▲	
	VCGX110304-NL	11	6.35	3.18	2.8	0.4	▲	
	VCGX160402-NL	16.5	9.525	4.76	4.4	0.2	▲	
	VCGX160404-NL	16.5	9.525	4.76	4.4	0.4	▲	
	VCGX160408-NL	16.5	9.525	4.76	4.4	0.8	▲	
	VCGX160412-NL	16.5	9.525	4.76	4.4	1.2	▲	
	VCGX220530-NL	22	12.7	5.56	5.5	3	▲	

Cermet Inserts



Insert Shape	Type	Dimension					Grade		
		LE	IC	S	D1	RE	OKE6220	OKE6210	
	Semi Finishing	CNMG120408-SAL	12.9	12.9	4.76	5.16	0.8	▲	▲
		TNMG160404-SAL	16.5	9.525	4.76	3.81	0.4	▲	▲
		TNMG160408-SAL	16.5	9.525	4.76	3.81	0.8	▲	▲
	VNMG160408-SAL	16.6	9.525	4.76	3.81	0.8	▲	▲	
	WNMG080404-SAL	8.7	12.7	4.76	5.16	0.4	▲	▲	
	WNMG080408-SAL	8.7	12.7	4.76	5.16	0.8	▲	▲	

Parting and Grooving Insert Naming Rule

Application Code

QC H V 03 02 R 05 —MP

Symbol	Application Code
QC	Grooving
QD	Part off
QR	Profile
QT	Parting & Grooving

Tools Holder Type

QC H V 03 02 R 05 —MP

Symbol	Width (mm)	Handle.
E	2	E
F	2.5	F E
G	3	G F E
H	4	H
J	5	J H
K	6	K J H
L	8	L

Corner Radius

QC H V 03 02 R 05 —MP

Symbol	Corner Radius
02	R0.2
03	R0.3
04	R0.4
05	R0.5
08	R0.8

Cutting Direction

QC H V 03 02 R 05 —MP

Symbol	Width (mm)
R	Right
L	Left
N	Neutral

Parting and Grooving Insert Naming Rule

Edge Number

QC H V 03 02 R 05 —MP

Symbol	Edge Number
W/D	2
V/S	1

Cutting Edge Width

QT H D 05 04 N —MG

Symbol	Width (mm)
05	5
06	6

Insert Angle

QC H V 03 02 R 05 —MP


Symbol	Angle
05	5°
07	7°

Chip Breaker

QC H V 03 02 R 05 —MG


MG	OC
	

Parting and Grooving Insert QT□□



Insert Shape	Type	Dimension			Grade	
		S ₀ ^{+0.1}	RE	La _{MAX}	OC4020	OP1215
	QTED02503N-MG	2.5	0.3	20.5	●	●
	QTFD0303N-MG	3	0.3	20.5	●	●
	QTGD0404N-MG	4	0.4	25.5	●	●
	QTHD0504N-MG	5	0.4	25.5	●	●
	QTKD0608N-MG	6	0.8	25.5	●	●

Parting and Grooving Insert QT□□



Insert Shape	Type	Dimension			Grade	
		S ₀ ^{+0.1}	RE	La _{MAX}	OC4020	OP1215
	QCFW0202N-OC	2	0.2	16	●	●
	QCFW02502N-OC	2.5	0.2	18.5	●	●
	QCGW0304N-OC	3	0.4	21	●	●
	QCHW0404N-OC	4	0.4	21	●	●
	QCJW0508N-OC	5	0.8	26	●	●

▲ Featured grade ● Optional grade

Threading Turning Insert Naming Rules

Cutting Direction

R/L/T 16 01 G A 60 M

RT	LT
right hand	left hand

Number of Teeth

R/L/T 16 01 G A 60 M

01	N
Single-teeth	N-teeth

Pitch Width

R/L/T 16 01 G A 60 M

	A	AG	G	N	Q		
mm	0.5-1.5	1.0-3.0	1.75-3.0	3.5-5.0	5.5-6.0		
TPI	48-16	26-10	14-8	7-5	4.5-4		

Insert Size

R/L/T 16 01 G A 60 M

L(mm)	IC(mm)	L(mm)	IC(mm)
6	3.97	16	9.525
8	4.76	22	12.7
11	6.35	27	15.875

Insert Type

R/L/T 16 01 G A 60 M

Symbol	Type
G	External threading
L	Internal threading

Threading Turning insert Naming Rules

Thread Profile

R/L/T 16 01 G A 60 M

Symbol	Thread Profile
55	55° general pitch thread
60	60° general pitch thread
ISO	ISO metric thread
UN	Unified thread (American standard thread)
W	Whitworth thread
BSPT	British standard taper pipe thread
NPT	NPT American standard taper pipe thread
UNJ	UNJ American standard aerospace and aviation thread
RD	30° DIN405 round thread
APIRD	Petroleum pipeline thread
TR	Trapeze30° 103 30° ISO metric thread
ACME	29° American standard ACME thread
STACME	29° American standard STACME thread



Production Method

R/L/T 16 01 G A 60 M

A	M
Full pressing	Full ground

Threading Insert

60° General Pitch Thread



▶ Application for insert

▶ Standard

it is suitable for all machining



▶ Tolerance grade

External thread		
Ground type	Applicative pitch	
	mm	TPI
R/LT0601G-A60M	0.5-1.25	48-16
R/LT1601G-A60M	0.5-1.5	48-16
R/LT1601G-AG60M	0.5-1.5	26-8
R/LT1601G-G60M	0.5-3.0	14-8
R/LT2201G-N60M	0.5-1.5	7-5
R/LT2701G-Q60M	0.5-3.0	4.5-4

Internal thread		
Ground type	Applicative pitch	
	mm	TPI
R/LT0601L-A60M	0.5-1.25	48-20
R/LT0801L-A60M	0.5-1.5	48-16
R/LT1101L-A60M	0.5-1.5	48-16
R/LT1101L-AG60M	1.0-2.5	26-9
R/LT1601L-A60M	0.5-1.5	48-16
R/LT1601L-AG60M	1.0-3.0	26-8
R/LT1601L-G60M	1.75-3.0	14-8
R/LT2201L-N60M	3.5-5.0	7-5
R/LT2701L-Q60-M	5.5-6.0	4.5-4

Threading Insert

55° General Pitch Thread



▶ Application for insert

▶ Standard

it is suitable for all machining



▶ Tolerance grade

External thread		
Ground type	Applicative pitch	
	mm	TPI
R/LT1101G-A55M	0.5-1.5	48-16
R/LT1601G-A55M	0.5-1.5	48-16
R/LT1601G-AG55M	1.0-3.0	26-8
R/LT1601G-G55M	1.75-3.0	14-8
R/LT2201G-N55M	3.5-5.0	7-5
R/LT2701G-Q55M	5.5-6.0	4.5-4

Internal thread		
Ground type	Applicative pitch	
	mm	TPI
R/LT0601L-A55M	0.5-1.25	48-20
R/LT0801L-A55M	0.5-1.5	48-16
R/LT1101L-A55M	0.5-1.5	48-16
R/LT1101L-AG55M	1.0-2.5	26-9
R/LT1601L-A55M	0.5-1.5	48-16
R/LT1601L-AG55M	1.0-3.0	26-8
R/LT1601L-G55M	1.75-3.0	14-8
R/LT2201L-N55M	3.5-5.0	7-5
R/LT2701L-Q55M	5.5-6.0	4.5-4

Threading Insert

ISO Metric Thread



► Application for insert

It is suitable for all machining



► Standard
MR262(DIN13)

► Tolerance grade
6g/6H

External thread				Internal thread			
Ground type	A type	Applicative pitch		Ground type	A type	Applicative pitch	
		mm	TPI			mm	TPI
				R/LT0601L-050ISOM		0.5	0.29
				R/LT0601L-075ISOM		0.75	0.43
				R/LT0601L-100ISOM		1.00	0.58
				R/LT0601L-125ISOM		1.25	0.72
				R/LT0801L-050ISOM		0.5	0.29
				R/LT0801L-075ISOM		0.75	0.43
				R/LT0801L-100ISOM		1.00	0.58
				R/LT0801L-125ISOM		1.25	0.72
				R/LT0801L-150ISOM		1.50	0.87
				R/LT0801L-175ISOM		1.75	1.01
R/LT1101G-050ISOM		0.50	0.31	R/LT1101L-050ISOM		0.50	0.29
R/LT1101G-075ISOM		0.75	0.46	R/LT1101L-075ISOM		0.75	0.43
R/LT1101G-080ISOM		0.8	0.49	R/LT1101L-080ISOM		0.8	0.46
R/LT1101G-100ISOM		1.00	0.61	R/LT1101L-100ISOM		1.00	0.58
R/LT1101G-125ISOM		1.25	0.77	R/LT1101L-125ISOM		1.25	0.72
R/LT1101G-150ISOM		1.50	0.92	R/LT1101L-150ISOM		1.50	0.87
R/LT1101G-175ISOM		1.75	1.07	R/LT1101L-175ISOM		1.75	1.01
R/LT1101G-200ISOM		2.00	1.23	R/LT1101L-200ISOM		2.00	1.15
R/LT1601G-050ISOM		0.50	0.31	R/LT1601L-050ISOM		0.50	0.29
R/LT1601G-075ISOM		0.75	0.46	R/LT1601L-075ISOM		0.75	0.43
R/LT1601G-080ISOM		0.80	0.49	R/LT1601L-080ISOM		0.80	0.46
R/LT1601G-100ISOM		1.00	0.61	R/LT1601L-100ISOM		1.00	0.58
R/LT1601G-125ISOM		1.25	0.77	R/LT1601L-125ISOM		1.25	0.72
R/LT1601G-150ISOM	RT1601G-150ISOA	1.50	0.92	R/LT1601L-150ISOM	RT1601L-150ISOA	1.50	0.87
R/LT1601G-175ISOM		1.75	1.07	R/LT1601L-175ISOM		1.75	1.01
R/LT1601G-200ISOM	RT1601G-200ISOA	2.00	1.23	R/LT1601L-200ISOM	RT1601L-200ISOA	2.00	1.15
R/LT1601G-250ISOM	RT1601G-250ISOA	2.50	1.53	R/LT1601L-250ISOM	RT1601L-250ISOA	2.50	1.44
R/LT1601G-300ISOM	RT1601G-300ISOA	3.00	1.84	R/LT1601L-300ISOM	RT1601L-300ISOA	3.00	1.73
R/LT1601G-350ISOM		3.50	2.15	R/LT1601L-350ISOM		3.50	2.02
R/LT2201G-350ISOM		3.50	2.15	R/LT2201L-350ISOM		3.50	2.02
R/LT2201G-400ISOM		4.00	2.45	R/LT2201L-400ISOM		4.00	2.31
R/LT2201G-450ISOM		4.5	2.76	R/LT2201L-450ISOM		4.5	2.60
R/LT2201G-500ISOM		5.00	3.07	R/LT2201L-500ISOM		5.00	2.89
R/LT2701G-550ISOM		5.50	3.37	R/LT2701L-550ISOM		5.50	3.17
R/LT2701G-600ISOM		6.00	3.68	R/LT2701L-600ISOM		6.00	3.46

Threading Insert

Unified Thread (American Standard Thread)



► Application for insert

It is suitable for all machining



► Standard
ANSI B1.1:74

► Tolerance grade
2A/2B

External thread			Internal thread		
Ground type	Applicative pitch		Ground type	Applicative pitch	
	mm	TPI		mm	TPI
			R/LT0601L-28UNM	28	0.52
			R/LT0601L-24UNM	24	0.61
			R/LT0601L-20UNM	20	0.73
			R/LT0601L-18UNM	18	0.81
			R/LT0801L-28UNM	28	0.52
			R/LT0801L-24UNM	24	0.61
			R/LT0801L-20UNM	20	0.73
			R/LT0801L-18UNM	18	0.81
			R/LT0801L-16UNM	16	0.92
R/LT1101G-28UNM	28	0.56	R/LT1101L-28UNM	28	0.52
R/LT1101G-24UNM	24	0.65	R/LT1101L-24UNM	24	0.61
R/LT1101G-20UNM	20	0.78	R/LT1101L-20UNM	20	0.73
R/LT1101G-18UNM	18	0.87	R/LT1101L-18UNM	18	0.81
R/LT1101G-16UNM	16	0.97	R/LT1101L-16UNM	16	0.92
R/LT1101G-14UNM	14	1.11	R/LT1101L-14UNM	14	1.05
R/LT1101G-12UNM	12	1.30	R/LT1101L-12UNM	12	1.22
R/LT1601G-48UNM	48	0.30	R/LT1601L-48UNM	48	0.31
R/LT1601G-40UNM	40	0.39	R/LT1601L-40UNM	40	0.37
R/LT1601G-32UNM	32	0.49	R/LT1601L-32UNM	32	0.46
R/LT1601G-28UNM	28	0.56	R/LT1601L-28UNM	28	0.52
R/LT1601G-24UNM	24	0.65	R/LT1601L-24UNM	24	0.61
R/LT1601G-20UNM	20	0.78	R/LT1601L-20UNM	20	0.73
R/LT1601G-18UNM	18	0.87	R/LT1601L-18UNM	18	0.81
R/LT1601G-16UNM	16	0.97	R/LT1601L-16UNM	16	0.92
R/LT1601G-14UNM	14	1.11	R/LT1601L-14UNM	14	1.05
R/LT1601G-12UNM	12	1.30	R/LT1601L-12UNM	12	1.22
R/LT1601G-11UNM	11	1.42	R/LT1601L-11UNM	11	1.28
R/LT1601G-10UNM	10	1.56	R/LT1601L-10UNM	10	1.47
R/LT1601G-9UNM	9	1.73	R/LT1601L-9UNM	9	1.63
R/LT1601G-8UNM	8	1.95	R/LT1601L-8UNM	8	1.83
R/LT2201G-7UNM	7	2.22	R/LT2201L-7UNM	7	2.09
R/LT2201G-6UNM	6	2.60	R/LT2201L-6UNM	6	2.44
R/LT2201G-5UNM	5	3.12	R/LT2201L-5UNM	5	2.93
R/LT2701G-4.5UNM	4.5	3.46	R/LT2701L-4.5UNM	4.5	3.26
R/LT2701G-4UNM	4	3.89	R/LT2701L-4UNM	4	3.67

Threading Insert

Whitworth Thread



Application for insert



It is suitable for all machining

- Standard
B.S.84:1956,
DIN259,ISO228/1:1982
- Tolerance grade
Medium class A

External thread				Internal thread			
Ground type	A type	Applicative pitch		Ground type	A type	Applicative pitch	
		mm	TPI			mm	TPI
				R/LT0601L-28WM		28	0.58
				R/LT0601L-24WM		24	0.68
				R/LT0601L-20WM		20	0.51
				R/LT0601L-19WM		19	0.90
				R/LT0801L-28WM		28	0.58
				R/LT0801L-24WM		24	0.68
				R/LT0801L-20WM		20	0.81
				R/LT0801L-19WM		19	0.90
				R/LT0801L-16WM		16	1.02
R/LT1101G-28WM		28	0.58	R/LT1101L-28WM		28	0.58
R/LT1101G-24WM		24	0.68	R/LT1101L-24WM		24	0.68
R/LT1101G-20WM		20	0.81	R/LT1101L-20WM		20	0.81
R/LT1101G-19WM		19	0.90	R/LT1101L-19WM		19	0.90
R/LT1101G-16WM		16	1.02	R/LT1101L-16WM		16	1.02
R/LT1101G-14WM		14	1.16	R/LT1101L-14WM		14	1.16
R/LT1101G-11WM		11	1.48	R/LT1101L-11WM		11	1.48
R/LT1601G-48WM		48	0.34	R/LT1601L-48WM		48	0.34
R/LT1601G-40WM		40	0.41	R/LT1601L-40WM		40	0.41
R/LT1601G-32WM		32	0.51	R/LT1601L-32WM		32	0.51
R/LT1601G-28WM		28	0.58	R/LT1601L-28WM		28	0.58
R/LT1601G-26WM		26	0.63	R/LT1601L-26WM		26	0.63
R/LT1601G-24WM		24	0.68	R/LT1601L-24WM		24	0.68
R/LT1601G-20WM		20	0.81	R/LT1601L-20WM		20	0.81
R/LT1601G-19WM		19	0.90	R/LT1601L-19WM		19	0.90
R/LT1601G-16WM		16	1.02	R/LT1601L-16WM		16	1.02
R/LT1601G-14WM	RT1601G-14WA	14	1.16	R/LT1601L-14WM	RT1601L-14WA	14	1.16
R/LT1601G-12WM		12	1.36	R/LT1601L-12WM		12	1.36
R/LT1601G-11WM	RT1601G-11WA	11	1.48	R/LT1601L-11WM	RT1601L-11WA	11	1.48
R/LT1601G-10WM		10	1.63	R/LT1601L-10WM		10	1.63
R/LT1601G-9WM		9	1.81	R/LT1601L-9WM		9	1.81
R/LT1601G-8WM		8	2.03	R/LT1601L-8WM		8	2.03
R/LT2201G-7WM		7	2.41	R/LT2201L-7WM		7	2.41
R/LT2201G-6WM		6	2.71	R/LT2201L-6WM		6	2.71
R/LT2201G-5WM		5	3.25	R/LT2201L-5WM		5	3.25
R/LT2701G-4.5WM		4.5	3.61	R/LT2701L-4.5WM		4.5	3.61
R/LT2701G-4WM		4	4.07	R/LT2701L-4WM		4	4.07

Threading Insert

British Standard Taper Pipe Thread



Application for insert



It is suitable for all machining

- Standard
B.S.21:1985
- Tolerance grade

External thread				Internal thread			
Ground type	Full pressed	Applicative pitch		Ground type	Full pressed	Applicative pitch	
		mm	TPI			mm	TPI
				R/LT0601L-28BSPTM		28	0.58
				R/LT0801L-28BSPTM		28	0.58
				R/LT0801L-19BSPTM		19	0.86
				R/LT1101L-19BSPTM		19	0.86
				R/LT1101L-14BSPTM		14	1.16
				R/LT1101L-11BSPTM		11	1.48
R/LT1601G-28BSPTM		28	0.58	R/LT1601L-28BSPTM		28	0.58
R/LT1601G-19BSPTM		19	0.86	R/LT1601L-19BSPTM		19	0.86
R/LT1601G-14BSPTM	RT1601G-14BSPTA	14	1.16	R/LT1601L-14BSPTM	RT1601L-14BSPTA	14	1.16
R/LT1601G-11BSPTM	RT1601G-11BSPTA	11	1.48	R/LT1601L-11BSPTM	RT1601L-11BSPTA	11	1.48

Threading Insert

NPT American Standard Taper Pipe Thread





- ▶ Application for insert
 - ▶ Standard USAS B2. 1:1968
 - ▶ Tolerance grade
- It is suitable for all machining

External thread			Internal thread		
Ground type	Applicative pitch		Ground type	Applicative pitch	
	mm	TPI		mm	TPI
			R/LT0601L-27NPTM	27	0.66
			R/LT0801L-27NPTM	27	0.66
			R/LT0801L-18NPTM	18	1.01
			R/LT1101L-18NPTM	18	1.01
			R/LT1101L-14NPTM	14	1.33
R/LT1601G-27NPTM	27	0.66			
R/LT1601G-18NPTM	18	1.01	R/LT1601L-18NPTM	18	1.01
R/LT1601G-14NPTM	14	1.33	R/LT1601L-14NPTM	14	1.33
R/LT1601G-11.5NPTM	11.5	1.64	R/LT1601L-11.5NPTM	11.5	1.64
R/LT1601G-8NPTM	8	2.42	R/LT1601L-8NPTM	8	2.42

Threading Insert

UNJ American Standard Aerospace and Aviation Thread





- ▶ Application for insert
 - ▶ Standard MIL-D-8879C
 - ▶ Tolerance grade 3A/3B
- It is suitable for all machining

External thread			Internal thread		
Ground type	Applicative pitch		Ground type	Applicative pitch	
	mm	TPI		mm	TPI
			R/LT0601L-18UNJM	18	0.74
			R/LT0801L-16UNJM	16	0.83
			R/LT0801L-14UNJM	14	0.95
			R/LT1101L-12UNJM	12	1.11
R/LT1601G-40UNJM	40	0.37			
R/LT1601G-36UNJM	36	0.41			
R/LT1601G-32UNJM	32	0.46			
R/LT1601G-28UNJM	28	0.52			
R/LT1601G-24UNJM	24	0.61			
R/LT1601G-20UNJM	20	0.73			
R/LT1601G-18UNJM	18	0.81			
R/LT1601G-16UNJM	16	0.92			
R/LT1601G-14UNJM	14	1.05			
R/LT1601G-12UNJM	12	1.22			
R/LT1601G-10UNJM	10	1.47	R/LT1601L-10UNJM	10	1.33
R/LT1601G-8UNJM	8	1.83	R/LT1601L-8UNJM	8	1.66
R/LT2201G-7UNJM	7	2.09	R/LT2201L-7UNJM	7	1.90
R/LT2201G-6UNJM	6	2.44	R/LT2201L-6UNJM	6	2.21
R/LT2201G-5UNJM	5	2.93	R/LT2201L-5UNJM	5	2.66
R/LT2701G-4.5UNJM	4.5	3.26	R/LT2701L-4.5UNJM	4.5	2.95
R/LT2701G-4UNJM	4	3.67	R/LT2701L-4UNJM	4	3.32

Threading Insert

30° DIN405 Round Thread



► Application for insert

It is suitable for all machining



► Standard
DIN405

► Tolerance grade
7h/7H

External thread			Internal thread		
Ground type	Applicative pitch		Ground type	Applicative pitch	
	mm	TPI		mm	TPI
R/LT1601G-10RDM	10	1.27	R/LT1601L-10RDM	10	1.27
R/LT1601G-8RDM	8	1.59	R/LT1601L-8RDM	8	1.59
R/LT1601G-6RDM	6	2.12	R/LT1601L-6RDM	6	2.12
R/LT2201G-6RDM	6	2.12	R/LT2201L-6RDM	6	2.12
R/LT2201G-4RDM	4	3.18	R/LT2201L-4RDM	4	3.18

Threading Insert

30° ISO Metric Thread



► Application for insert



It is suitable for all machining

► Standard
DIN103

► Tolerance grade
7e/7H

External thread			Internal thread		
Ground type	Applicative pitch		Ground type	Applicative pitch	
	mm	TPI		mm	TPI
R/LT1601G-1.5TRM	1.5	0.90	R/LT1601L-1.5TRM	1.5	0.90
R/LT1601G-2TRM	2	1.25	R/LT1601L-2TRM	2	1.25
R/LT1601G-3TRM	3	1.75	R/LT1601L-3TRM	3	1.75
R/LT2201G-4TRM	4	2.25	R/LT2201L-4TRM	4	2.25
R/LT2201G-5TRM	5	2.75	R/LT2201L-5TRM	5	2.75
R/LT2701G-6TRM	6	3.50	R/LT2701L-6TRM	6	3.50
R/LT2701G-7TRM	7	4.00	R/LT2701L-7TRM	7	4.00

Petroleum Pipeline Threading insert



► Application for insert

It is suitable for all machining



► Standard
STD.5B.1979

► Tolerance grade

external thread			internal thread		
ground type	applicative pitch		ground type	applicative pitch	
	mm	TPI		mm	TPI
R/LT1601G-10APIRDM	10	1.41	R/LT1601L-10APIRDM	10	1.41
R/LT1601G-8APIRDM	8	1.81	R/LT1601L-8APIRDM	8	1.81

Threading Insert

29° American ACME Thread



► Application for insert

It is suitable for all machining

► Standard
ANSI B1.5:1988



► Tolerance grade
3G

External thread		
Ground type	Applicative pitch	
	mm	TPI
R/LT1601G-12ACMEM	12	1.19
R/LT1601G-10ACMEM	10	1.52
R/LT1601G-8ACMEM	8	1.84
R/LT2201G-6ACMEM	6	2.37
R/LT2201G-5ACMEM	5	2.79
R/LT2701G-4ACMEM	4	3.43

Internal thread		
Ground type	Applicative pitch	
	mm	TPI
R/LT1601L-8ACMEM	8	1.84
R/LT2201L-6ACMEM	6	2.37
R/LT2201L-5ACMEM	5	2.79
R/LT2701L-4ACMEM	4	3.43

Threading Insert

29° American STACME Thread



► Application for insert

It is suitable for all machining

► Standard
ANSI B1.8:1988

► Tolerance grade
2G

External thread		
Ground type	Applicative pitch	
	mm	TPI
R/LT1601G-12STACMEM	12	0.76
R/LT1601G-10STACMEM	10	1.02
R/LT1601G-8STACMEM	8	1.21
R/LT2201G-6STACMEM	6	1.52
R/LT2201G-5STACMEM	5	1.78
R/LT2701G-4STACMEM	4	2.16
R/LT2701G-3STACMEM	3	2.79

Internal thread		
Ground type	Applicative pitch	
	mm	TPI
R/LT2201L-5STACMEM	5	1.78
R/LT2701L-4STACMEM	4	2.16
R/LT2701L-3STACMEM	3	2.79

D-1 Technical Information

Turning Tools

Recommend Collocation of General Turning Grades and Chip Breakers

	ISO P Steel	ISO M Stainless Steel	ISO K Cast Iron	ISO S Cast Iron
Finishing	OPF — OC2115	OMF — OP1215 — OP1315		SMM — OP1105
	OTF — OC2115	OTF — OP1215 — OP1315		OP6215
		MSF — OP1215 — OP1315	OKM — OC3210	
Semi Finishing	OPM — OC2125	MF — OP1215 — OP1315	OC3215	
	OC2325	OMM — OC4315 — OP1215	General chip breaker — OC3210	
	OC2325S	OP1315	OC3215	OSM — OP1105
	OTM — OC2125	OTM — OP1215 — OP1315		OP6215
Roughing	OC2325		OKR — OC3215	
	OC2325S		OC3220	
	OPR — OC2125		Fit (None chip breaker) — OC3215	
	OC2325S		OC3220	
	OTR — OC2125			
	OC2325			
	OC2325S			

Recommended Cutting Parameters on Different Grades

ISO	P类 IOS P		
Materials	Carbon steel	Alloy steel	Hardened and tempered steel
Hardness	HB120-180	HB180-240	HB240-350

ISO	IOS M	
Materials	Austenite	Martensite
Hardness	HB120-200	HB330

ISO	IOS K	
Materials	Grey cast Iron	Nodular cast Iron
Hardness	HB150-220	HB140-220

ISO	IOS N
Materials	Aluminium alloy
Hardness	HB60

Recommended Cutting Parameters on Different Grades

Materials \ Grade		OC2015	OC2025	OC2115	OC2125
Carbon steel	Vc(m/min)	450-200	430-180	480-260	460-240
Alloy steel		320-140	300-130	340-150	330-150
Hardened and tempered steel		200-80	190-70	220-80	210-70

Materials \ Grade		OC4015	OC4025	OC4225	OP1205
Austenite	Vc(m/min)	200-100	190-90	210-110	220-100
Martensite		200-140	210-130	220-140	260-170










Materials \ Grade		OC3015	OC3115D	OC3215	
Grey cast Iron	Vc(m/min)	280-160	400-190	380-200	
Nodular cast Iron		280-140	300-150	220-110	

Grade	OK434			
Vc(m/min)	900-400			

Common Problems and Solutions for Turning


FAQ		Reason	Solutions		Insert Grade		Cutting Conditions				Tool Shape					Setting/ Machine		
			Harder Grade	Tougher Grade	Vc	Fn	Ap	Coolant	Chip Breaker Review	Rake Angle	Corner Radius	Setting Angle	Edge Strength	Change to Higher Tolerance	Toolholder Rigidity	Workpiece/Tool Installation	Overhang Length	Power, Rigidity
Too Much Wear On Nose	Accuracy Out Tolerance	Wear Increase at Flank Wear	○															
		Unsuitable Cutting Conditions			↓	↑												
Surface Accuracy Deterioration	POOR Roughness Of Surface	Tool weariness Increasing, Cutting Edge not Sharp	○		↓			○		↑	↑	↓	○					
		Cutting Edge Chipping		○		↓	↓			○		↑			○	○	○	
		Unsuitable Geometry							○		↑		↓	○				
		Unsuitable Cutting Conditions			↑	↓	↓	○										
		Vibration, Chattering		○	↑↓	↓	↓	○	○	↑	↓	↑	↓		○	○	○	○
Heat	Cutting Heat Factors	Unsuitable Cutting Conditions			↓	↓	↓											
		Unsuitable Geometry	○						○	↑			↓					
Deterioration of Accuracy	Variation of Dimension	Unsuitable Insert Accuracy											○					
		Position Offset of Workpiece and Tool							○	↑	↓	↑			○	○	○	○
Edge Damage	Wear Increase at Relief Face	Flank Wear	○		↓				○	↑	↑	↓						
		Rake Face Wear	○		↓	↓	↓		○	↑		↓						
	Chipping		○		↓	↓		○			↓	↑		○	○	○	○	
	Built-up Edge	Unsuitable Workpiece Hardness and Cutting Conditions			↑	↑		○	○	↑		↓	○					
	Comp Cracks	Unsuited Tool's Material and Cutting Condition to Workpiece Material			↓	↓	↓	○	○	↑		↓						
	Edge Nose Deformation	Interrupted Cutting	○		↑	↓	↓	○	○	↑	↑	↓	↓					
	Tool Life	Unsuited Material and Cutting Condition		○		↓	↓		○		↑	↓	↑		○	○	○	○
Chip Control	Long, Tangling Chips	Unsuitable Cutting Conditions			↓	↑	↑											
		Unsuitable Material and Cutting Conditions							○		↓	↑						
	Chips Scattering	Unsuitable Cutting Conditions				↓	↓	○										
Burns Turned-down Edge	Steel, Aluminum-Burr	Unsuitable Cutting Conditions			↑	↓		○										
		Insert Wear, Unsuitable Geometry	○						○	↑	↓	↑	↓					
	Iron Cast, Turned-down Edge	Unsuitable Cutting Conditions			↓	↑		○										
		Insert Wear, Unsuitable Geometry	○						○	○	↓	↓	↓					
Soft Steel, Turned-down Edge	Unsuitable Cutting Conditions				↓	↓												
	Insert Wear, Unsuitable Geometry	○						○	↑	↑		↑		○	○	○	○	

Tool Wear and Solution

Tool Wear Types	Situation	Reason	Solutions
Flank Wear	Higher cutting resistance Notch wear on flank Poor roughness of surface or deterioration of accuracy. 	Soft grades Excessive cutting speed Small flank angle Low feed	Select a higher wear-resistant grade Reduce cutting speed Increase flank angle Increase feed
Crater Wear	Uncontrolled chip Poor surface quality when finishing High speed processing carbon steel 	Soft grades Excessive cutting speed Excessive feed The strength of chip breaker insufficient	Change to a higher wear-resistant grade Reduce cutting speed Reduce feed Select a higher strength chip breaker
Chipping	Sudden fracture of cutting edge (rake face and flank) Instability insert life 	Toughness insufficient Excessive feed rate Strength of cutting edge insufficient Instability of the tool	Select a tougher grade Decrease feed rate Increase honing of cutting edge (chamfering to rounding) Increase the stability and setting angle
Insert Fracture	Cutting resistance increased Poor surface roughness 	Toughness insufficient Excessive feed rate Strength of cutting edge insufficient Instability of the tool	Select a tougher grade Decrease feed rate Increase honing of cutting edge (chamfering to rounding) Increase the stability and setting angle
Plastic Deformation	Variation of dimension Nose wear, cutting edge drape or passivating when processing alloy steel Poor surface roughness 	Soft grade Excessive cutting speed Excessive cutting depth and feed rate Overheat on cutting edge	Select a higher red hardness cutting material Decrease cutting speed Decrease cutting depth and feed rate Select a higher thermal conductivity cutting material(CVD+sufficient coolant)
Build-Up-Edge	Workpiece dissolve with Cutting edge Poor surface roughness when finishing Cutting resistance increased Cutting soft materials 	Cutting speed too low Cutting edge obtuse Unsuitable tool material	Increase cutting speed Increase rake angle Select small sticking force
Thermal Crack	Crack by heat cycle (often happen in milling and interrupted cutting) 	Toughness of tool grade insufficient Swell and shrink by cutting heat(cold-thermocycling)	Cutting without coolant/Sufficient coolant Select a tougher and more thermal shock resistance grade
Flaking	Often in instability cutting and cutting high-hardness materials 	Build-up edge Uncontrolled chip	Increase rake angle Increase chip breaker
Notch Wear	Notch partial failure Partial cratering 	Processing hardened material, oxide-scale, superalloy	Select a higher wear-resistance CVD grade Adopt taper cutting (variable cutting depth) Decrease setting angle

The Names of Each Part of Turning Tool

Names of Turning Holder Parts



Effects of Rake Angle

Larger rake angle makes cutting edge sharper. reduces resistant forces of chip flow. diminishes friction and prevent deformation. leading to smaller, less abrasion and higher surface quality. However, too large rake angle would reduce the rigidity and strength of tool. Heat can't be diffused easily, Serious breakage and abrasion on tool would occur, reducing tool life. Please choose rake angle according to machining conditions.

Value selection	Situations
Small rake angle	When machining brittle and hard materials: When roughing and interrupted cutting
Big rake angle	When machining Plastic or soft materials: When finishing:

The Names of Each Part of Turning Tool

Effects of Clearance Angle

The main function of clearance angle to reduce the friction between the clearance face of tool and the surface of workpiece. When the rake angle is fixed, larger clearance angle can increase and the achieve higher surface quality. However, if clearance angle is too large, the strength of cutting edge would decrease. Also, heat can't be diffused easily and serious abrious would occur, reducing tool life.

The principle of choosing clearance angle: Choose small clear-ance angle if friction is not serious


Value selection	Situations
Small clearance angle	In order to increase nose strength when roughing When machining brittle and hard materials
Large clearance angle	In order to reduce friction when finishing When machining materials easy to be hardened:

The Names of Each Part of Turning Tool

Effects of Inclined Angle


Positive or negative inclined angle determines the direction of chip flow, and also affects the strength and impact resistance of insert nose.

As diagram(1) shows, when the inclined angle is negative, namely nose is in the lowest point as apposed to the bottom of tool, chips flow to the machined surface of workpiece.



Negative inclined angle

As diagram(2) shows, when inclined angle is positive, namely the nose is in the highest point as apposed to the bottom of the tool, chips flow to the areas of workpiece surface that haven't been machined.



Positive inclined angle

The change of inclined angle also affects insert nose strength and impact resistance. When the inclined angle is negative, the nose is in the lowest point of cutting edge. When the cutting edge enters the workpiece, the contacting point is on the cutting edge or rake face, protecting the nose from impact and increasing the strength of the nose. Normally, negative inclined angle should be chosen for tools with big rake angle. This can not only increase nose strength, but also prevent the impact of entry.


The Names of Each Part of Turning Tool

Effects of Approach Angle

Reduces approaching angle increases the strength of tools and enable heat to diffuse easily, improving surface quality. This is because when the approach angle is small, cutting edge width is large, and then the unit width of cutting edge bears less cutting force. Meanwhile, tool life can be improved.

Normally, select 90° approach angle for turning of slender and step shaft; select 45° approach angle for external turning. End surface machining and chamfering. When approach angle is larger, radial force is reduced, cutting is stable, cutting thickness is increased, and chip breaking is excellent.

Value selection	Situations
Small approach	For those materials with high intensity, high hardness and hardened layer on the surface
Big approach angle	When rigidity of the machine is not enough



The Names of Each Part of Turning Tool

Effects of Minor Angle

Minor angle is the main angle that can affect surface quality, and it can also affect tool strength. If the approach angle is too small, the friction between the secondary flank and machined surface of workpiece will increase, causing vibration.

The principle of selecting minor angle: Select small minor angle when roughing or when the friction is unaffected and is on vibration. Select large minor angle when finishing.

Nose Radius

Nose radius significantly affects nose strength and surface quality. Large nose radius means higher cutting edge strength, and the abrasion on the rake face and clearance face can be reduced to some extent. However, if the nose radius is too large, radial force will increase, and vibration is easy to occur, affecting machining precision and surface quality.

Value selection	Situations
Small nose radius	Finishing at small cutting depth Machining parts such as slender shaft When the rigidity of the machine is not enough
Large nose radius	When roughing / When machining hard materials (intermittent cutting) When the rigidity of the machine is not enough

Tool Wear and Solution

Calculation of Cutting Speed




$$V_c = \frac{\pi \times D \times n}{1000} \text{ (m/min)}$$

In the formula: V_c : Cutting speed (m/min)
 n : Rotating speed of main axle (rev/min)
 D : Diameter of workpiece (mm)
 For example: When the rotating speed is 280 rev/min and the diameter of workpiece is 150 mm, the cutting speed should be:

$$V_c = \frac{\pi \times D \times n}{1000} = \frac{3.14 \times 150 \times 280}{1000} = 132 \text{ (m/min)}$$

Calculation of Feed Rate



$$f = \frac{l}{n} \text{ (mm/rev)}$$

In the formula: f : Feed rate per rotation (mm/rev)
 L : Cutting length per minute (mm/min)
 N : Rotating speed of main axle (rev/min)
 For example: When the rotating speed of main axle is 500 rev/min, and the cutting length per minute is 100 mm/min, the feed rate per rotating should be:

$$f = \frac{l}{n} = \frac{100}{500} = 0.2 \text{ (mm/rev)}$$

Tool Wear and Solution

Cutting Time Calculation of External and Internal Turning




$$T = \frac{l}{f \times n} \text{ (min)}$$

In the formula: T: Cutting time(min)
 L: length of machined areas(mm)
 F: Feed rate(mm/rev)
 N: Rotating speed of main axle(rev/min)
 For example: When the rotating speed of main axle is 250rev/min, and the feed rate is 2.0mm/rev,the time needed for a cutting length of 150mm should be:

$$T = \frac{l}{f \times n} = \frac{150}{0.2 \times 250} = 3 \text{ (min)}$$

Time Calculation End Surface Turning (Constant Linear Speed)




$$T = \frac{\pi \times (a^2 - b^2)}{4000 \times Vc \times f} \text{ (min)}$$

In the formula: T: Cutting time(min)
 Vc: length of machined areas(mm)
 F: Cutting speed
 For end surface without hole, b=0, the formula is still Valid.

Tool Wear and Solution

The Oretical Value Calculation of Machined Surface Roughness



$$R = \frac{f^2}{8r_c} \times 1000 (\mu m)$$


In the formula: R: Theoretical roughness value of machined surface
 F: Feed rate (mm/rev)
 Rc: Nose radius (mm)
 For example: When the feed rate is 0.2mm/rev, and the nose radius is 0.4mm, the theoretical roughness value of machined surface should be:

$$R = \frac{f^2}{8r_c} \times 1000 = \frac{0.2^2}{8 \times 0.4} \times 1000 = 12.5 (\mu m)$$

Tool Wear and Solution

Effects of Three Main Parameters

Normally, short machining time, long tool life and high machining precision are expected in machining, so the material quality, hardness, and shape of the workpiece, and properties of machine should be fully considered and then we can select suitable tools and adopt high-efficiency cutting parameters, namely three parameters.



Cutting Speed (V_c)

When the workpiece is rotating on the machine, the number of its rotation per minute is defined as Rotating speed of main axle (n). Because of its rotation, the cutting speed measured on the contacting point of diameter is defined as linear speed. m/min . Normally, linear speed is considered to measure the effect of cutting speed on machining.

Effect of Cutting Speed

Cutting speed has significant effect in tool life. When the cutting speed is increased, cutting temperature will increase and tool life will be shortened. Cutting speed varies according to the different types and hardness of work-piece. The below conclusions are reached after many cutting experiments:

- (1) Normally tool life would be reduced to half when the cutting speed is increased by 20%. Tool life would be 20% of the original life if the cutting speed is raised by 50%.
- (2) Low speed (20-40 m/min) cutting could easily cause vibration and shorten tool life.

Tool Wear and Solution

Feed Rate (f_n)

Feed rate is defined as the moving distance of tool after workpiece rotates for one circle, measured by $mm/rotation$.

Feed Rate (f_n)

Feed rate is a key factor that determines surface quality. Meanwhile it also affects the range of chip forming and the thickness of chips during machining. In terms of the effect on tool life, small feed rate leads to serious abrasion on clearance face, reducing tool life.

Cutting Depth (a_p)

Cutting depth is defined as the difference between machined surface and unmachined surface. Measured by mm . It is half the difference value between the original diameter and machined diameter.

Effect of Cutting Depth


Cutting depth should be determined by the machining allowance and shape of workpiece, power and rigidity of machine, and tool rigidity. The change of cutting depth has little effect on tool life. If the cutting depth is too low, the cutting nose only scrapes the hardened layer on the workpiece surface, reducing tool life. When there is a hardened oxide layer on the workpiece surface, higher cutting depth should be adopted within the possible range of machine's power to avoid cutting nose just cutting the hardened layer of workpiece.

Stainless Steel Cutting Application Cases




Stainless steel flange

Customer: XX Company
 Workpiece: Stainless steel flange(no hole)
 Workpiece material: 304L
 Lathe type: CSK50A
 OKE insert: CNMG120412-MF/OP1215
 Compare insert: A well-known manufacturer
 Cooling type: Fluid cooling
 Processing content: End face rough turning
 Cutting parameter: $V_c = 180 \text{ m/min}$, $F_n = 0.28 \text{ mm/r}$, $A_p = 2.2 \text{ mm}$




Stainless Steel Cutting Application Cases




Stainless steel flange

Customer: XX Company
 Workpiece: Hubbed flange
 Workpiece material: SUS304L
 Lathe type: HTC1635i
 OKE insert: WNMG060412-OMM/OP1215
 Compare insert: A well-known manufacturer
 Cooling type: Fluid cooling
 Processing content: Taper, end face(semi-finishing)
 Cutting parameter: $V_c = 160 \text{ m/min}$, $F_n = 0.18 \text{ mm/r}$, $A_p = 1.5 \text{ mm}$




Stainless steel flange

Customer: XX Company
 Workpiece: Flange
 Workpiece material: SUS304
 Lathe type: HTC1635i
 OKE insert: WNMG060412-MSF/OP1315
 Compare insert: A well-known manufacturer
 Cooling type: Fluid cooling
 Processing content: End face fine finishing
 Cutting parameter: $V_c = 200 \text{ m/min}$, $F_n = 0.28 \text{ mm/r}$, $A_p = 0.6 \text{ mm}$



Stainless steel flange

Customer: XX Company
 Workpiece: Flange
 Workpiece material: 45#Forge piece
 Lathe type: CNC lathe
 OKE insert: WNMG080412-OMM/OP1215
 Compare insert: A well-known manufacturer
 Cooling type: No
 Processing content: End face turning
 Cutting parameter: $V_c = 258 \text{ m/min}$, $F_n = 0.2 \text{ mm/r}$, $A_p = 1.25 \text{ mm}$




Stainless Steel Cutting Application Cases



Stainless steel flange

Customer: XX Company
Workpiece: Flange
Workpiece material: SUS316
Lathe type: CNC lathe
OKE insert: WNMG060412-MF/OC4315
Compare insert: A well-known manufacturer
Cooling type: Cooling liquid
Processing content: End face rough turning, remove black skin
Cutting parameter: $V_c=200$ m/min, $F_n=0.28-0.33$ mm/r, $A_p=0.2-0.8$ mm

Cutting life comparison





Steel Cutting Application Cases



Steel

Customer: XX Company
Workpiece: Hub Bearing Unit(outer ring)
Workpiece material: 55# forge steel
Lathe type: CY-K800H
OKE insert: WNMG080412-OPM/OC2125
Compare insert: A well-known manufacturer
Cooling type: No
Processing content: End face and external rough turning
Cutting parameter: $V_c=260$ m/min, $F_n=0.28$ mm/r, $A_p=1.3$ mm


Cutting life comparison




Steel

Customer: XX Company
Workpiece: Bearing outer ring
Workpiece material: Gcr15
Lathe type: SK50P
OKE insert: WNMG080412-Z/OC2325
Compare insert: A well-known manufacturer
Cooling type: Fluid cooling
Processing content: External semi-finishing turning
Cutting parameter: $V_c=393$ m/min, $F_n=0.176$ mm/r, $A_p=1.0$ mm

Cutting life comparison




Steel Cutting Application Cases




Steel
Customer: XX Company
Workpiece: Bearing outer ring
Workpiece material: Gcr15
Lathe type: SK50P
OKE insert: WNMG080408-Z/OC2325
Compare insert: A well-known manufacturer
Cooling type: Fluid cooling
Processing content: External finishing turning
Cutting parameter: $V_c = 340 \text{ m/min}$, $F_n = 0.18 \text{ mm/r}$, $A_p = 0.5 \text{ mm}$



Steel Cutting Application Cases



Steel
Customer: XX Company
Workpiece: Cross bearing
Workpiece material: 55# forge steel
Lathe type: Horizontal CNC lathe
OKE insert: WNMG080408-OPM/OC2125
Compare insert: A well-known manufacturer
Cooling type: Emulsion fluid cooling
Processing content: End face, external
Cutting parameter: $V_c = 79 \text{ m/min}$, $F_n = 0.4 \text{ mm/r}$, $A_p = 1.25 \text{ mm}$





Steel
Customer: XX Company
Workpiece: Outer bearing
Workpiece material: 65# forge steel
Lathe type: Horizontal CNC lathe
OKE insert: WNMG080412-OPM/OC2125
Compare insert: A well-known manufacturer
Cooling type: No
Processing content: End face, and external
Cutting parameter: $V_c = 160\text{--}220 \text{ m/min}$, $F_n = 0.2\text{--}0.28 \text{ mm/r}$, $A_p = 1.0 \text{ mm}$




Steel
Customer: XX Company
Workpiece: Spindle
Workpiece material: 20CrMoH
Lathe type: Horizontal CNC lathe
OKE insert: TNMG160408-OPR/OC2115
Compare insert: A well-known manufacturer
Cooling type: No
Processing content: External roughing turning
Cutting parameter: $V_c = 138\text{--}218 \text{ m/min}$, $F_n = 0.24\text{--}0.36 \text{ mm/r}$, $A_p = 1 \text{ mm}$

Steel Cutting Application Cases




Steel

Customer: XX Company
Workpiece: Spindle
Workpiece material: 20CrMoH
Lathe type: Horizontal CNC lathe
OKE insert: VNMG160404-OPF/OC2115
Compare insert: A well-known manufacturer
Cooling type: No
Processing content: External roughing turning
Cutting parameter: $V_c = 132\text{--}181\text{ m/min}$, $F_n = 0.12\text{--}0.24\text{ mm/r}$, $A_p = 0.5\text{ mm}$




Steel

Customer: XX Company
Workpiece: The outer cylinder
Workpiece material: 30CrMnSi
Lathe type: Horizontal CNC lathe
OKE insert: CNMG160608-OPM/OC2125
Compare insert: A well-known manufacturer
Cooling type: No
Processing content: External roughing turning
Cutting parameter: $V_c = 138\text{ m/min}$, $F_n = 0.4\text{ mm/r}$, $A_p = 3\text{ mm}$




Cast iron Cutting Application Cases




Cast iron

Customer: XX Company
Workpiece: Air Compressor Flange
Workpiece material: HT250
Lathe type: SK50P
OKE insert: WNMG080412/OC3215
Compare insert: A well-known manufacturer
Cooling type: No
Processing content: External and end face roughing turning
Cutting parameter: $V_c = 550\text{ m/min}$, $F_n = 0.35\text{ mm/r}$, $A_p = 1.2\text{ mm}$




Cast iron

Customer: XX Company
Workpiece: Brake disc
Workpiece material: G3000
Lathe type: i5T3
OKE insert: TNMG220416-GH/OC3215
Compare insert: A well-known manufacturer
Cooling type: No
Processing content: End face semi-finishing turning
Cutting parameter: $V_c = 706\text{ m/min}$, $F_n = 0.32\text{ mm/r}$, $A_p = 1.0\text{ mm}$




Cast iron Cutting Application Cases




Cast iron

Customer: XX Company
Workpiece: Air compressor flange
Workpiece material: HT250
Lathe type: Horizontal CNC lathe
OKE insert: WNMG080412/OC3215
Compare insert: A well-known manufacturer
Cooling type: No
Processing content: External and end face turning
Cutting parameter: $V_c = 356 \text{ m/min}$, $F_n = 0.28 \text{ mm/r}$, $A_p = 1 \text{ mm}$



Cast iron

Customer: XX Company
Workpiece: Brake drum
Workpiece material: HT250
Lathe type: Horizontal CNC lathe
OKE insert: WNMG080408/OC3215
Compare insert: A well-known manufacturer
Cooling type: No
Processing content: Endface and external rough turning
Cutting parameter: $V_c = 230\text{--}290 \text{ m/min}$, $F_n = 0.3\text{--}0.45 \text{ mm/r}$, $A_p = 2\text{--}3 \text{ mm}$




Milling Application Cases




Milling

Customer: XX Company
Workpiece: Turbine blade
Workpiece material: 22Cr12NiWMoV-5
Lathe type: HSTM-500-HD
OKE insert: APKT170516R-QG/OP1312
Compare insert: A well-known manufacturer
Cooling type: Fluid cooling
Processing content: Profile Milling
Cutting parameter: $V_c = 241 \text{ m/min}$, $V_f = 3500 \text{ mm/min}$, $A_p = 1.2 \text{ mm}$, $A_e = 16 \text{ mm}$




Milling

Customer: XX Company
Workpiece: Gimbal Joint
Workpiece material: 30CrMnSiNi2A
Lathe type: V1850
OKE insert: APMT1135PDER-M2/OP1130
Compare insert: A well-known manufacturer
Cooling type: Fluid cooling
Processing content: Finishing face milling and profile milling
Cutting parameter: $V_c = 120 \text{ m/min}$, $V_f = 3500 \text{ mm/min}$, $A_p = 0.18 \text{ mm}$, $A_e = 2 \text{ mm}$




Milling Application Cases



Milling


Customer: XX Company
Workpiece: Side panel mold
Workpiece material: 45#
Lathe type: CNC gantry milling
OKE insert: APMT1604PDER-H2L/OP1215
Compare insert: A well-known manufacturer
Cooling type: Compressed air
Processing content: U-groove, square groove machining, parting
Cutting parameter: $V_c = 94 \text{ m/min}$, $F_n = 1.04 \text{ mm/r}$, $A_p = 0.3\text{--}0.35 \text{ mm}$

Threading Application Cases




Thread

Customer: XX Company
Workpiece: Joint
Processing industry: Valve
Workpiece material: SUS201
Lathe type: Wenzhou Eastsea CNC
OKE insert: RT1601L-11WA/OP1205
Compare insert: A well-known manufacturer
Processing content: Internal threading turning
criterion of changing tool: Insert wear
Cutting fluid: Yes
Cutting parameter: $V_c = 75\text{--}83 \text{ m/min}$ $F_n = 2.309 \text{ mm/r}$



Milling

Customer: XX Company
Workpiece: Side panel mold
Workpiece material: 45#
Lathe type: CNC gantry milling
OKE insert: RPMT1204MO-JSL/OP1315
Compare insert: A well-known manufacturer
Cooling type: Compressed air
Processing content: U-groove, square groove machining, parting
Cutting parameter: $V_c = 138 \text{ m/min}$, $F_n = 0.96 \text{ mm/r}$, $A_p = 0.45 \text{ mm}$



Thread

Customer: XX Company
Workpiece: Elbow
Machining Industry: Valve
Workpiece material: 304
Lathe type: KIND
OKE insert: RT1601L-14WA/OP1205
Compare insert: A well-known manufacturer
Processing content: Internal threading turning
criterion of changing tool: Insert wear
Cutting fluid: Yes
Cutting parameter: $V_c = 58\text{--}65 \text{ m/min}$ $F_n = 1.814 \text{ mm/r}$

E-5

Technical Information

General Technical Reference

Selection Method of Cutting Tool

Selection Method of General Turning Tools:

- 1.Understand the processed material condition,Machine Model and condition.
- 2.Select the suitable insert shape,setting angle and clamoins designation.
- 3.According to above conditions select details of tools as L/R,dimension,etc.
- 4.Select the type,chip break and grade of insert according to all conditions.

Selection Method of Parting and Grooving tools:

- 1.Understand the processed material condition,Machine Model and condition.
- 2.Select the insert type according to processing methods(external,internal,face grooving)
- 3.According to above conditions select details of tools as L/R, dimensions,etc.
- 4.Select the type,clamping designation,chip break and grade of insert according to all conditions

Selection Method of Threading Tools:

- 1.Understand the processed material condition,Machine Model and condition.
- 2.Select the tool type according to thread's type,processing methods,etc.
- 3.According to above conditions select details of cutting tools as L/R,dimension,etc.
- 4.Select the type,chip break and grade of Insert according to all condition

Selection Method of Cutting Tool

Selection Method of Milling Tool Specifications:

1. The first step is to understand the material condition, machine type and state you need to process.
2. Determine the basic type of milling tool according to the processing method(plane milling, Square shoulder milling, imitation milling, milling slot, corner milling, etc.).
3. According to the machining precision and the shape and size of the machining surface and other factors to determine the use of the overall milling cutter or transposable milling cutter.
4. According to the above factors and your machine model to determine the interface, dimensions and other details of the tool.
5. Finally determine the blade specification, groove type, and brand number corresponding to the above factors.

Selection Method for Hole Processing Tool Specifications:

1. Understand the material condition, machine type and state you need to process.
2. Determine the basic types of hole cutting tools(drilling, boring, hinge, thread processing, etc.) according to the processing process.
3. According to the machining accuracy and the dimension of the machining hole, it is determined that the whole tool or the fork-turning tool is used.
4. According to the above factors and your machine model to determine the interface, dimensions and other details of the tool.
5. Finally determine the insert specification, groove type, and brand number corresponding to the above factors.

The Correction Coefficient Table Of Hardness and Cutting Speed

Material	Theoretical Hardness	The Correction Coefficient Table Of Hardness and Cutting Speed									
		Hardness Decrease ← Hardness Difference(Measured Difference - Theoretical Difference) → Hardness Increase									
		-60	-40	-20	0	20	40	60	80	100	
P	HB180	1.42	1.24	1.11	1.00	0.91	0.84	0.77	0.72	0.67	
M	HB180	1.44	1.25	1.11	1.00	0.91	0.84	0.78	0.73	0.68	
K	Grey Cast Iron	HB220	1.21	1.13	1.06	1.00	0.95	0.9	0.86	0.82	0.79
	Nodular Cast Iron	HB250	1.33	1.21	1.09	1.00	0.91	0.84	0.75	0.7	0.65
N	HB75			1.05	1.00	0.95					
S	HB350			1.12	1.00	0.89					
HRC			-6	-3	0.00	3	6	9			
H	HRC60		1.10	1.02	1.00	0.96	0.93	0.9			

Actual Processing Speed=Recommended Processing Speed*Correction Factor Of Cutting Speed

Recommended Cutting Parameters See Packaging

i.e. Cutting general alloy steel, hardness HB180, CNMG120404-OPF/OC2015, the recommended cutting speed is $V=250\text{m/min}$. When measured hardness is HB220, the hardness difference is 40(220-180). Find The corresponding speed correction coefficient is 0.84 on above table, and then the actual processing speed $V_c=250*0.84=210\text{mm/min}$

The Correction Coefficient Table Of Insert Life and Cutting Speed

Insert Life Insert Material	The Correction Coefficient Table Of Insert Life and Cutting Speed					
	10	15	30	45	60	90
OC2015	1.12	1.00	0.82	0.73	0.67	0.6
OC2025	1.11	1.00	0.84	0.76	0.71	0.64
OC2035	1.11	1.00	0.84	0.76	0.70	0.63
OC2115	1.25	1.00	0.68	0.54	0.46	0.37
OC2125	1.55	1.00	0.47	0.30	0.22	0.14
OP1205	1.15	1.00	0.82	0.74	0.69	0.64
OP1215	1.10	1.00	0.85	0.72	0.65	0.62
OP1030	1.10	1.00	0.85	0.72	0.65	0.62
OC4025	1.19	1.00	0.75	0.63	0.56	0.47
OC4315	1.22	1.00	0.73	0.61	0.54	0.45
OC3105	1.11	1.00	0.70	0.60	0.50	0.40
OC3215	1.22	1.00	0.80	0.65	0.60	0.55
OC3115D	1.25	1.00	0.72	0.63	0.52	0.41
OP2202	1.20	1.00	0.84	0.70	0.63	0.59

Actual Processing Speed=Recommended Processing Speed*Correction Factor Of Cutting Speed

i.e. Cutting general alloy steel, CNMG120404-OPF/OC2015, the recommended cutting speed is V=250m/min (the standard life is 15 min). If the insert life of 60 mins is expected, find the speed correction coefficient is 0.67 on above table, and then the actual processing speed is Vc=250*0.67=167.5m/min.

Comparison Table for Turning Insert Chipbreaker

Negative Inserts

ISO	Processing Category	OKE	TaeguTec	KENNAMETAL	HITACHI	ZCCCT	SANDVIK	TUNGALOY	KYOCERA	KORLOY	SUMITOMO	mitsubishi
P	Superfinishing	R/L-F	FA	FF	FE		QF,LC	01, F	DP,GP,PP, VF,XP, XP-T,XF	VL	FA,FB, FL	PK,FH,FP, FY,FS
	Finishing	OPF 53 Z	FG,FA	FN	BE, B, CE, BH	DF	XF,PF,	TS,TSF,ZF 11,NS,AS, TQ,NM,CS	DP,GP,PP	VF,VB	SU, LU, FE	LP,C, SA, SH
	Finishing(Soft Steel)	OPF	FC	FN		SF		17,TS,NS,CB 11, 27, ZF	XQ,XS	VL	FL	SY
	Finishing(Wiper)		WS	FW		WGF	WL,WF	AFW,FW, ASW,SW	WF,WP	HW	LUW,SEW	SW
	Semifinishing	OPM KPM	MP,MC, PC,MT	MN	CT,AB, AH,AY,AE	DM,PM	PM,QM, XM	TM,AM,DM, ZM,TA	PG,GS,PS	VM,MP	GU (UG) UX, GE	MP,MA
	Light Roughing	OPR	RT,通槽	RN,RP	RE, Y	DR LR	PR,HM XMR	TH,THS	PH	B25,HR, GR	MU, MX, UX	GH,RP, 通槽
	Roughing	OPR OPH	RX,RH,HD, HT,HY,HZ	MR, RN, RP	TE,UE,HX, HE,H	DR HDR	QR,MR PR,HR	TI,TRS, TUS	PX	GH,VH, VT	HG,HP,HU, HW,HF	HZ, HL,HM, HX,HR,HV

Comparison Table for Turning Insert Chipbreaker

Negative Inserts

ISO	Processing Category	OKE	TaeguTec	KENAMETAL	HITACHI	ZCCCT	SANDVIK	TUNGALOY	KYOCERA	KORLOY	SUMITOMO	mitsubishi
M	Finishing	OMF MSF	EA,SF	FP,FF	MP,AB,BH	EF	MF	SF,SA,SS	MQ,SQ	VP2,MP	SU,EF	SH,LM
	Semifinishing	OMM MF	ET,EM	MP,UP	PV,DE,SE,AH	EM	MM,QM, XM,K	SM,S,TA	MU,MS, TK,SX	HS,MM	EX,EG,GU	MS,GM, MM,MA,ES
	Roughing	OMR		MR,RP,P	AE	ER	MR	TH,SH,TU		GA,RM	HM,EM,MU	GH, HZ, RM,HL,HZ
K	Finishing	OKM	MT	FN	VA,AH	PM	KF	CF,TA		MP	UZ	LK,MA
	Semifinishing	TK,OKM Without chipbreaker	MG,RT	RP,UN	V,AE	PM	KM	CM	KQ,KG, C,	B25,MK	GZ(UX)	MK,GK,
	Roughing	OPR,平板	KT,RT	平板	RE	平板	KR,KRR	CH,平板	KH,GC,ZS	MA,RK		PK, 平板
S	Finishing	OSF	EA,SF	FS			SF	HRF	MQ	VP2	EF	FJ
	Semifinishing	OSM	ML,MP, SU,MK	NG,UP,MS		VI	NGP,SM	HRM, HMM,SA	SQ,MS, MU,TK	VP3	EG,EX	MS
	Roughing	OSM		RP			SR,SMR		SG,SX	VP4	MU,EM	RS,GJ

Comparison Table for Turning Insert Chipbreaker

Positive Inserts

ISO	Processing Category	OKE	TaeguTec	KENAMETAL	HITACHI	ZCCCT	SANDVIK	TUNGALOY	KYOCERA	KORLOY	SUMITOMO	mitsubishi
P	Finishing	OTF	FA,SA,FG	LF,FP	JQ	SF,HF	PF,UF,XF	01,PF FS,JS	PF,DP,GP, PP,VF	VL,VF	FC,FB, LU(FP,FK)	FP,FV, LP,SV
	Finishing(Wiper)		WS	FW			WF		WP		LUW,SDW	SW
	Semifinishing	OTM	PC,MT, PMR	MF,MP	JE	HM	XM,PM, UM,PR,XR	PM,PS,PF PSF,PSS 23,24	HQ,GK,	HMP,MP	MU	MV,MP, 全周
	Semifinishing(Wiper)	OTR	WT	MW			WM,PR, UR,KM					MW
M	Finishing	MSF,OTF		FP,FF	MP	EF	MF	SS&	CF,CK,GQ, GF,MQ,SK	VP1	FC	FM,LM
	Semifinishing	OTM		MP,UP		EM	MM	PM	HQ,GK	VL	MU	MM, 通槽
K	Semifinishing	OTM		MW,平板		HR,HM, 平板	KM,KR,KF	CM CM Without chipbreaker	平板	MP	MU	MK,通槽, 平板
S	Finishing			GT-LF,R,GV, GT-HP		NF,NSF	SF,01			VP1		FS,LS, FS-P, LS-P,FJ, LS,MS
	Semifinishing	OSM		MT-LF,R,GV-T, MT-FP			MM,QM, SMR		MQ	VL	SI	
N	General cutting	NL,AK	FL	GT-HP,GT-LF, GW-F,GW-E		LH	AL	PP,AL	AH	AK,AR	AG,AW,AY	AZ

Material Comparison

Steel

ISO	Nations And Standard										
	GB (P类)	W-nr	DIN	AISI/SAE	BS	EN	UNI	UNE	SS	AFNOR	JIS
Carbon Steel	15	1.0401	C15	1015	080M15		C15C16	F.111	1350	CC12	
	20	1.0402	C22	1020	050A20	2C	C20C21	F.112	1450	CC20	
	35	1.0501	C35	1035	060A35		C35	F.113	1550	CC35	
	45	1.0503	C45	1045	080M40		C45	F.114	1650	CC45	
	55	1.0535	C55	1055	070M55		C55		1655		
	60	1.0601	C60	1060	080A62	43D	C60			CC55	
	Y15	1.7015	9SMN28	1213	230M07		CF9SMn28	11SMn28	1912	S250	SUM22
Manganese Steel	40Mn	1.1157	40Mn4	1039	150M36	15				35M5	
	25	1.1158	Ck25	1025							S25C
	35Mn2	1.1167	36Mn5	1335				36Mn5	2120	40Mn5	SMn438(H)
	30Mn	1.117	28Mn6	1330	150M28	14A	C28Mn			20M5	SCMn1
	35Mn	1.1183	Cf35	1035	060A35		C36		1572	XS38TS	S35C
	1.0718	9SMnPb28	12L13				CF9MnPb28	11SMnPb28	1914	S250Pb	SUM22L
	1.0722	10SPb20					CF10Pb20	10SPb		10PbF2	
	1.0726	35S20	1140	212M36	8M		F210G	1957	35MF4		
Y13	1.0736	9SMn36	1215	240M07	1B	CF9SMn36	12SMn35			S300	
	1.0737	9SMnPb36	12L14				CF9SMnPb36	12SMnPb35	1926	S300Pb	
55Si2Mn	1.0904	55Si9	9255	250A53	45	55Si8	56Si7	2085	55S7		
	1.0961	60SiCr7	9262			60SiCr8	60SiCr8		60SC7		
15	1.1141	Ck15	1015	080M15	32C	C16	C15K	1370	XC12	S15C	
Ck45	1.1191	45	1045	080M46		C45	C45K	1672	XC42	S45C	
55	1.1203	Ck55	1055	070M55		C50	C55K		XC45	S55C	
50	1.1213	Cf53	1050	060A52		C53		1674	XC48TS	S50C	
60Mn	1.1221	Ck60	1060	080A62	43D	C60		1678	XC60	S68C	
	1.1274	Ck101	1095	060A96				1870		SUP4	
	1.3401	X120Mn12		Z120M12		XG120Mn12	X120Mn12		X120M12	SCMnH/1	
Gr15,45Gr	1.3505	100Cr6	52100	534A99	31	100Cr6	F.131	2258	100C6	SUJ2	
	1.5415	15Mo3	ASTMA204Gr,A	1501-240		16Mo3KW	16Mo3	2912	15D3		
	1.5426	16Mo5	4520	1503-245-420		16Mo5	16Mo5				
	1.5622	14Ni6	ASTMA350LF5			14Ni6	15Ni6		16N6		
	1.5662	X8Ni9	ASTM A353	1501-509:510		X10Ni9	XBNI09				

Material Comparison

Steel

ISO	国家和标准 Nations And Standard										
	GB (P类)	W-nr	DIN	AISI/SAE	BS	EN	UNI	UNE	SS	AFNOR	JIS
Nickel Chromium Steel		1.5680	12Ni19	2515						Z18N5	
		1.5710	36NiCr6	3135	640A35	111A				35NC6	SNC236
		1.5732	14NiCr10	3415			16NiCr11	15NiCr11		14NC11	SNC415(H)
		1.5752	14NiCr14	3415, 3310	655M13 655A12	36A				12NC15	SNC815(H)
Nickel Chromium Molybdenum Steel		1.6511	36CrNiMo4	9840	816M40	110	38CrNiMo4(KB)	35CrNiMo4		40NCD3	
		1.6523	21NiCrMo2	8620	850M20	362	20NiCrMo2	20NiCrMo2	2503	20NCD2	SNCM220(H)
		1.6546	40NiCrMo2	8740	311-Type7		40NiCrMo2(KB)	40NiCrMo2			SNC240
	40CrNiMoA	1.6582	34CrNiMo6	4340	817M40	24	35CrNiMo6(KB)		2541	35NCD6	
	1.6587	17CrNiMo6		820A16			14CrNiMo13		18NCD6		
Chromium Steel	15Cr	1.7015	15Cr3	5015	523M15					12C3	SCr415(H)
	35Cr	1.7033	34Cr4	5132	530A32	18B	34Cr4(KB)	35Cr4		32C4	SCr430(H)
	40Cr	1.7035	41Cr4	5140	530M40	18	41Cr4	42Cr4		42C4	SCr440(H)
	40Cr	1.7045	42Cr4	5140				42Cr4	2245		SCr440
Manganese Chromium Steel	18CrMn	1.7131	16MnCr15	5115	527M20		16MnCr15	16MnCr15	2511	16MC5	
	20CrMn	1.7176	55Cr3	5155	527A60	48				55C3	SUP9(A)
	30CrMn	1.7218	25CrMo4	4130	1717CDS110		25CrMo4(KB)	55Cr3	2225	25CD4	SCM420; SCM430
	35CrMo	1.722	34CrMo4	4137, 4135	708A37	19B	35CrMo4	34CrMo4	2234	35CD4	SCM432 SCR3M3
	40CrMoA	1.7223	41CrMo4	4140, 4142	708M40	19A	41CrMo4	41CrMo4	2244	42CD4TS	SCM440
	42CrMo, 42CrMnMo	1.7225	42CrMo4	4140	708M40	19A	42CrMo4	42CrMo4	2244	42CD4	SCM440(H)
Chromium Molybdenum Steel		1.7262	15CrMo5					12CrMo4	2216	12CD4	SCM415(H)
		1.7335	13CrMo44	ASTM A182 F11 F12	1501-620Cr. 27		14CrMo44	14CrMo45		15CD3.5;15CD4.5	
		1.7361	32CrMo12		722M24	40B	32CrMo12	F.124.A	2240	30CD12	
		1.738	10CrMo910	ASTM A182 F22	1501-622Cr.31;45		12CrMo9,10	TU.H	2218	12CD9;10	
		1.7715	14MoV63		1503-660-440			13MoCrV6			
	50CrVA	1.8159	50CrV4	6150	735A50	47	50CrV4	51CrV4	2230	50CV4	SUP10
		1.8509	41CrAlMo7		905M39	41B	41CrAlMo7	41CrAlMo7	2940	40CAD6,12	
	1.8523	39CrMoV139		897M39	40C	36CrMoV12					

Material Comparison

Steel

ISO	Nations And Standard										
	GB (P类)	W-nr	DIN	AISI/SAE	BS	EN	UNI	UNE	SS	AFNOR	JIS
Steel	T10	1.1545	C105W1	W.110			C98KU C100KU	F.515 F.516	1880	Y1105	
	T12A	1.1663	C125W	W.112			C120KU	(C120)		Y2120	SK2
	CrV,9SiCr	1.2067	100Cr6	L3	BL3			100Cr6		Y100C6	
	Cr12	1.208	X210Cr12	D3	BD3		X210Cr13KU X250Cr12KU	X210Cr12		Z200Cr12	SKD1
	4Cr5MoVSi	1.2344	X40CrMoV51	H13	BH13			X40CrMoV5	2242	Z40CDV5	SKD61
	Cr6WV	1.2363	X100CrMoV51	A2	BA2		X35CrMoV05KU X40CrMoV51KU	X100CrMoV5	2260	Z100CDV5	SKD12
	CrWMo	1.2419	105WCr6				X100CrMoV51KU	105WCr5	2140	105WC13	SKS31 SKS2 SKS3
	Cr12W	1.2436	X210CrW12				10WCr6 107WCr5KU	X210CrW12	2312		SKD2
	5CrNiMo	1.2542	45WCrV7	S1	BS1		X215CrW121KU	45WCrS8	2710		
	3Cr2W8V	1.2581	X30WCrV93 X30WCrV93KU	H21	BH21		45WCrV8KU	X30WCrV9		Z30WCV9	SKD5
	Cr12MoV	1.2601	X165CrMoV12				X28W09KU X30WCrV93KU	X160CrMoV12	2310		SKD11
	5CrNiMo	1.2731	55NiCrMoV6	L6			X165CrMoV12KU	F.250.S		55NCDV7	SKT4
	V	1.2833	100V1	W210	BW2					Y1105V	SKS43
	W6Mo5Cr4V2Co5	1.3243	S6-5-2-5					HS6-5-2-5	2723	Z85WDCV	SKH55
	W18Cr4VCo5	1.3255	S18-1-2-5	T4	BT4		HS6-5-2-5	HS18-1-1-5		Z80WCV 10-05-04-1	SKH3
	W6Mo5Cr4V2	1.3343	S6-5-2S	M2	BM2		X78WCo1805KU	HS6-5-2	2722	Z85WDCV 06-05-04-02	SKH9
		1.3348	S2-9-2	M7		Z	X82WMo0605KU	HS-2-9-2	2782	Z100WCWV 09-02-04-02	
	W18Cr4V	1.3355	S18-0-1	T1	BT1		HS2-9-2	HS18-0-1		Z80WCV 18-04-01	SKH2
	W6Mo5Cr4V3		S6-5-3	M3			X75W18KU				SKH52
			M42	BM42						SKH59	

Material Comparison

Steel

ISO	国家和标准 Nations And Standard						
	GB (P类)	W-nr	DIN	JIS	DAIDO	AISI/SAE	
Die Steel					PX5N	P20mod	
					NAK55		
					NAK80		
		3Cr13			SUS420J2mod	S-STAR	420mod
					SKS93	YK30	2
		9CrWMn			SKS3mod	GOA	01mod
		Cr12MoV	X165CrMoV12		SKD11	DC11	D2
					SKD11mod	DC53	D2mod
		4Cr5MoSiV1	X40CrMoV51		SKD61	DHA1	H13
						DH21	
						DH31-S	
					DH2F		

Material Comparison

Stainless Steel

ISO	国家和标准 Nations And Standard										
	GB (P类)	W-nr	DIN	AISI/SAE	BS	EN	UNI	UNE	SS	AFNOR	JIS
Stainless Steel	0Cr13;1Cr12	1.4000	X6Cr13	403	403S17		X6Cr13	F.3110	2301	Z6C13	SUS403
		1.4001	X7Cr14					F.8401			
	1Cr13	1.4006	X10Cr13	410	410S21	56A	X12Cr13	F.3401	2302	Z10C14	SUS410
	1Cr17	1.4016	X6Cr17	430	430S15	60	X8Cr17	F.3113	220	Z8C17	SUS430
	2Cr13	1.4021	X20Cr13	410	S62	56B; 56C	X20C13	F.3401		Z20C13	SUS410
		1.4027	G-X20Cr14		420C29	56B				Z20C13M	SCS2
	4Cr13	1.4034	X46Cr13		420S45	56D	X40Cr14	F.3405	2304	Z40CM;Z38C13M	SUS420J2
	1Cr17Ni2	1.4057	X20CrNi172	431	431S29	57	X16CrNi16	F.3427	2321	Z15CNi6.02	SUS431
	Y1Cr17	1.4104	X12CrMoS17	430F			X10CrS17	F.3117	2383	Z10CF17	SUS430F
	1Cr17Mo	1.4113	X6CrMo171	434	434S17		x8CrMo17		2325	Z8CD17.01	SUS434
		1.4313	X5CrNi134		425C11					Z4CND13.4M	SCS5
		1.4408	G-X6CrNiMo1810		316C16			F.8414			SCS14
	4Cr9Si2	1.4718	X45CrSi93	HW3	401S45	52	X45CrSi8	F.322		Z45CS9	SUH1
	0Cr13Al	1.4724	X10CrAl13	405	403S17		X10CrAl12	F.311		Z10C13	SUS405
	Cr17	1.4742	X10CrAl18	430	430S15	60	X8Cr17	F.3113		Z10CAS18	SUS430
8Cr20Si2Ni	1.4757	X80CrNiSi20	HNV6	443S65	59	X80CrSiNi20	F.320V		Z80CSN20.02	SUH4	
2Cr25N	1.4762	X10CrAl24	446			X16Cr26		2322	Z10CAS24	SUH446	
Stainless Steel	0Cr18Ni9	1.4301	X5CrNi1810	304	304S15	58E	X5CrNi1810	F.3551 F.354 F.3504	2332	Z6CN18.09	SUS304
	1Cr18Ni9MoZr	1.4305	X10CrNiS189	303	303S21	58M	X10CrNiS18.09	F.3508	2346	Z10CNF18.09	SUS303
	0Cr19Ni10	1.4306	X2CrNi1911	304L	304S12		X2CrNi18.11	F.3503	2352	Z2CN18.10	SCS19
		1.4308	G-X6CrNi189		304C15					Z6CN18.10M	SCS13
	Cr17Ni7	1.4310	X12CrNi177	301			X12CrNi1707	F.3517	2331	Z12CN17.07	SUS301
		1.4311	X2CrNiN1810	304LN	304S62				2371	Z2CN18.10	SUS304LN
	0Cr19Ni9	1.4350	X5CrNi189	304	304S31	58E	X5CrNi1810			Z6CN18.09	SUS304
	0Cr17Ni11Mo2	1.4401	X5CrNiMo1712	316	316S16	Z6CND17.11	X5CrNiMo1712	F.3543	2347	1.4401	SUS316
	00Cr17Ni13Mo2	1.4429	X2CrNiMoN17133	316LN					2375	Z2CND17.13	SUS316LN
	0Cr27Ni12Mo3	1.4435	X2CrNiMo18143	316L	316S12		X2CrNiMo1713		2353	Z2CDN17.13	SCS16
	00Cr19Ni13Mo3	1.4438	X2CrNiMo17133	317L	317S12		X2CrNiMo18.16		2367	Z2CND19.15	SUS317L
		1.4460	X8CrNiMo275	329L					2324		SUS329L; SCH11 SCS11
	1Cr18Ni9Ti	1.4541	X6CrNiTi1810	321	2337	321S12	X6CrNiTi1811	F.3553	58B	Z6CNT18.10	SUS321
	1Cr18Ni11Nb	1.4550	X6CrNiNb1810	347	347S17	58F	X6CrNiTi1811	F.3552	2338	Z6CNNb18.1	SUS347
	Cr18Ni12Mo2Ti	1.4571	X6CrNiMoTi17122	316Ti	320S17	58J	X6CrNiMoTi17	F.3535	2350	Z6NDT17.12	
Stainless Steel		1.4581	G-X5CrNiMoNb1810		318C7		XG8CrNiMo18			Z4CNDNb1812M	SCS22
	Cr17Ni12Mo3Nb	1.4583	X10CrNiMoNb1812	318			X6CrNiMoTiNb17			Z6CNDNb1713B	
	1Cr23Ni13	1.4828	X15CrNiSi2012	309	309S24					Z15CNS20.1	SUH309
	0Cr25Ni20	1.4845	X12CrNi2521	310S	310S24		X6CrNi2520	F.331	2361	Z12CN2520	SUH310
	Cr15Ni36W3Ti	1.4864	X12NiCrSi3616	330						Z12CN35.1	SUH330
		1.4865	G-X40NiCrSi3818		330C11		XG50NiCr3919				SCH15
	5Cr2Mn9Ni4N	1.4871	X53CrMnNiN219	EV8	349S54;321S12	58B	X53CrMnNiN219			Z52CMN21.0	SUH35
1Cr18Ni9Ti	1.4878	X12CrNiTi189	321	321S320	58C	X6CrNiTi1811	F.3523		Z6CNT18.12	Su321	

Material Comparison

Cast Iron

ISO	国家和标准 Nations And Standard										
	GB (P类)	W-nr	DIN	AISI/SAE	BS	EN	UNI	UNE	SS	AFNOR	JIS
Nodular Iron	QT400-18		GGG40	60-40-18	400/17		GS370-17	FGE38-17	0717-02	FGS370-17	FCD400
	QT450-10			65-45-12	420/12		GS400-13	FGE42-12		FGS400-12	FCD450
	QT500-7		GGG50	70-50-05	500/7		GS500-7	FGE50-7	0727-02	FGS500-7	FCD500
	QT600-3		GGG60	80-60-03	600/7		GS600-2	FGE60-2	0732-03	FGS600-2	FCD600
	QT700-2		GGG70	100-70-03	700/2		GS700-2	FGE70-2	0737-01	FGS700-2	FCD700
	QT800-2		GGG80	120-90-02	800/2		GS800-2	FGE80-2	0864-03	FGS800-2	FCD800
	QT900-2				900/2						
Grey Cast Iron			GG40	NO.60					0140	FGL400	FC350
	HT350		GG35	NO.50	350	G35	FG35	0135	FGL350	FC300	
	HT300		GG30	NO.45	300	G30	FG30	0130	FGL300	FC250	
	HT250		GG25	NO.35	250	G25	FG25	0125	FGL250	FC200	
	HT200		GG20	NO.30	200	G20	FG20	0120	FGL200	FC150	
	HT150		GG15	NO.20	150	G15	FG15	0115	FGL150	FC100	
	Ht100				100	G10		0110			

Grade Comparison

	ISO Code	OKE	ZCCCT	MITSUBISHI	Korloy	TaeguTec	SUMITOMO	TUNGALOY	KYOCERA	HITACHI	SANDVIK	KENNAMETAL
CVD Turning	P01			UE6105		TT8105	AC8015P AC810P	T9205 T9105	CA510 CA5505	HG8010	GC4305 GC4315	KCP05B KCP05 KCPK05 KCK05B KCK05 KCK15B KCK15
	P10	OC2015 OC2115 OC2325	YBC151 YBC152	UE6105 MC6015 UE6110 MY5015	NC3215	TT8105 TT8115	AC8015P AC810P	T9205 T9105 T9215 T9115	CA510 CA515 CA5505 CA5515	HG8010	GC4305 GC4315 GC4325	KCP05B KCP05 KCPK05 KCP10B KCP10 KCK15B KCK15 KCK20B
	P20	OC2025 OC2125 OC2325	YBC251 YBC252	MC6015 UE6110 MC6025 UE6020 MY5015	NC3225 NC3120	TT5100 TT8125	AC8025P AC820P	T9215 T9115 T9225 T9125	CA025P CA525 CA5515 CA5525 CR9025	HG8025 IP2000 GM25	GC4315 GC4325 GC4225 GC1515	KCP10B KCP10 KCP25B KCP25 KCM15B KCM15
	P30	OC2035 OC2125 OC2135	YBC252 YBC351 YBC352	MC6025 UE6020 MC6035 UE6035 UH6400	NC3030	TT8125 T5100	AC8035P AC830P AC6030M AC630M	T9225 T9125 T9235 T9135 T6130	CA025P CA525 CA5525 CA530 CA5535 CR9025	IP3000 GM8035	GC4315 GC4325 GC4335 GC2025	KCP25B KCP25 KCP30B KCP30 KCM15B
	P40	OC2035	YBC351 YBC352	MC6035 UE6035 UH6400	NC5330	TT8135 TT7100	AC8035P AC830P AC6030M AC630M		CA530 CA5535	GM8035 GX30	GC4325 GC4335	KCP30B KCP30 KCP40B KCP40 KCM25B KCM25 KCM35B KCM35
	M10	OC4015 OC4315		MC7015 US7020	NC9115	TT9215	AC6020M AC610M	T9235 T9135 T6130	CA6515	IP1050S	GC2015 GC1515	KCM15B KCM15
	M20	OC4025 OC4225	YBM151 YBM153	MC7015 US7020 MC7025	NC9115 NC9125	TT9225	AC6020M AC6030M AC610M AC630M	T9215 T9115	CA6525	IP1050S	GC2015 GC2025 GC2020	KCP30B KCP30 KCP40B KCP40 KCM15B KCM15 KCM25B KCM25
	M30	OC4035	YBM151 YBM251	MC7025 US735	NC9125 NC9135	TT9235	AC6030M AC630M AC8035P AC830P	T6120 T9215 T9115		IP100S GX30	GC2025 GC2020	KCP40B KCP40 KCM25B KCM25 KCM35B KCM35
	M40		YB253	US735	NC9135	TT9235	AC6030M AC630M	T6130		IP100S GX30		KCM35B KCM35
	K01	OC3105	YBD052	MC5005 UC5105	NC6310	TT7005	AC4010K AC405K	T5105	CA310 CA4010 CA4505 CA5505	HX3505	GC3210	KCK05B KCK05
	K10	OC3115D OC3215	YBD102	MC5015 UC5115 MY5015	NC6310 NC6315	TT7015	AC4010K AC4015K AC405K AC415K	T5105 T515 T5115 T9215	CA310 CA315 CA4010 CA4115 CA4505 CA4515 CA5505	HX3505 HX3515 HG8010	GC3210	KCK05B KCK05 KCK15B KCK15
	K20	OC3115D OC3215	YBD152 YBD252	MC5015 UC5115 UE6110 MY5115	NC6315	TT7015 TT7025	AC4015K AC415K AC420K AC425K AC8025P	T515 T5115 T5125 T9215	CA315 CA320 CA4115 CA4120 CA4515	HX3515 HG8010	GC3210 GC3225	KCK15B KCK15 KCK20B KCK20
	K30	OC3125		UE6110				T5125	CA320	HG8010	GC3225	KCP05B KCP05 KCPK05 KCP10B KCP10 KCP25B KCP25 KCK20B KCK20

Grade Comparison

	ISO Code	OKE	ZCCCT	MITSUBISHI	Korloy	TaeguTec	SUMITOMO	TUNGALOY	KYOCERA	HITACHI	SANDVIK	KENNAMETAL
CVD Milling	P10					TT7515	ACP2000 ACP100				GC4220 GC4230 GC3040	KC930M KC935P
	P20		YBC301 YBC251	F7030 MC7020	NC5330	TT7515	ACP2000 ACP100	T3225			GC4220 GC4230 GC3040	SC6525 SP6519
	P30	OC4025 OC4225	YBM351	F7030 MC7020	NC5330 NC5340 NCM325	TT7800	ACP2000 ACP100	T3130 T3225			GC4230 GC3040 GC2040 M30B	MP91M SC6525 KCPK30 X500
	P40	OC4035	YBC302		NC5340 NC325 NCM325 NC5350 NCM335	TT7800					GC4240 GC4230 GC3040 GC2040 M30B	KCPK30 X500
	M10						ACM200					
	M20	OC4025 OC4225	YBM251 YBM253	F7030 MC7020	NC5330		ACM200	T3225	CA6535	GX2160 AX2040	GC2040 GC4230	SC6525
	M30	OC4035	YBM302	F7030 MC7020	NC5330 NC5340 NCM325 NC5350	TT7800	ACM200	T3225 T3130			GC2040 GC4230 GC4240 M30B S40T	SC6525 X500
	M40				NCM335 NC5350	TT7800					GC2040 M30B S40T GC4240	X500
	K10	OC3105 OC3115	YBD151	MC5020		TT7515	ACK2000 ACK100 ACK200	T1215 T1115				SC3025 KCK15
	K20	OC3115D OC3115	YBD252	MC5020	NC5330	TT7515	ACK200 ACK200	T1215	CA420M	GX2120	GC3220 K20W	KCK15 SC3025 MP91M
	K30	OC3125	YBD252		NC5340						GC3040	MP91M KCPK30 SC6525

Grade Comparison

	ISO Code	OKE	ZCCCT	MITSUBISHI	Korloy	TaeguTec	SUMITOMO	TUNGALOY	KYOCERA	HITACHI	SANDVIK	KENNAMETAL
PVD Turning	P10	OP1102	YBG102	VP10MF MS6015	PC8105		AC1030U ACZ150 AC5025S AC520U	AH710	PR930 PR1005 PR1025 PR1115 PR1215 PR1425 PR1225		GC1025 GC1125	KCS10 KCU10 KC5010
	P20	OP1205	YBG202	VP10RT VP20RT VP15TF VP20MF	PC8110 PC230	TT9020 TT9030	AC1030U AC5025S AC520U AC530U	AH120 AH725 AH730 SH725 SH730 J740	PR930 PR1025 PR1115 PR1215 PR1225 PR1625	IP2000	GC1025 GC1125	KCS10 KCU10 KCU25 KC5010 KC5025
	P30	OP1302	YBG202	VP10RT VP20RT VP15TF VP20MF	PC5300 PC8115	TT8020 TT8080 TT9030	AC1030U AC530U	AH120 AH725 AH7025 AH730 SH725 SH730 GH730 GH330 J740	PR1025 PR1225 PR1535	IP3000 CY250	GC1025 GC1125	KCU25 KC5025
	P40					TT8020 TT8080 TT9080	AC1030U	AH120 AH725 AH645		IP3000	GC1025	
	M10	OP1102 OP1205 OP1305	YBG202 YBG205	VP10MF MS6015	PC8105 PC8110	TT5080	AC515S AC5025S AC510U AC520U ACZ150	AH8005 AH630	PR1025 PR1215 PR1225	IP050S IP100S JP9105 JP9115	GC1115 GC1125	KCS10 KCU10 KC5010
	M20	OP1202 OP1215 OP1315 OP1525	YBG202 YBG205	VP10RT VP20RT VP15TF VP20MF	PC8110 PC8110 PC5300	TT5080 TT9080	AC5015S AC5025S AC1030U AC520U	AH8015 AH630 AH120 AH7025 AH725 SH725 SH730	PR930 PR1025 PR1125 PR1215 PR1425 PR1225 PR1515	IP100S HS9115	GC1115 GC1125 GC2035	KCS10 KCU10 KCU25 KC5010 KC5025
	M30	OP1205H OP1215 OP1302		VP10RT VP20RT VP15TF VP20MF MP7035	PC9030 PC5300 PC5400	TT8020 TT8080 TT9020 TT9080	AC5025S AC6040M AC1030U AC520U AC530U	AH645 AH120 AH725 SH725 SH730 J740	PR1125 PR1535		GC1125 GC2035	KCU25 KC5025
	M40			MP7035	PC5400	TT8020 TT8080 TT9020 TT9080	AC6040M AC1030U AC530U	AH645		GX30	GC2035	
	K10	OP1102					AC1030U AC510U ACZ150	GH110 AH110	PR905 PR1215	HX3305 HG3305 HX3515 HG8010 TH315 ATH10E	GC3330 GC3220 K20W K20D K20M K15W	KCS10 KCU10 KC5010
	K20	OP1202		VP10RT VP20RT VP15TF	PC5300		AC1030U AC510U AC530U ACZ150	AH120 AH7025	PR905 PR1215		GC3330 GC3220 GC3040 K20W K20D GC4230 K20M K15W	KCS10 KCU10 KCU25 KC5010 KC5025
	K30			VP10RT VP20RT VP15TF			AC1030U AC530U	AH120 GH130			GC3330 GC3040 K20W GC4240 GC4230	

Grade Comparison

	ISO Code	OKE	ZCCCT	MITSUBISHI	Korloy	TaeguTec	SUMITOMO	TUNGALOY	KYOCERA	HITACHI	SANDVIK	KENNAMETAL
PVD Turning	P10		YBG252		PC2005 PC2010 PC2015	TT2510 TT7080	ACP2500 ACP200	AH120 AH725	PR830 PR1025 PR1225	PCA12M PN15M PN215 JP4115	GC1010 GC1025 GC1030	KC5010M KC515M
	P20	OP1205 OP1305 OP2202	YBG202 YBG205 YBG9320 YBG252	MP6120 VP15TF	PC2505 PC2510	TT2510 TT7080 TT8020 TT9030 TT9080	ACP3000 ACU2500 ACP200 ACP300	AH120 AH725 AH3135 AH9030 AH3225 AH9130	PR1525 PR830 PR1025 PR1225 PR1230	CY150 CY9020 JP4120	GC1025 GC1030 GC2030	KC522M KC525M KCSM30 SP6519
	P30	OP1030 OP1130 OP1215 OP1302 OP1315 OP1325	YBG302	MP6120 VP15TF MP6130 VP30RT	PC3600 PC3500 PC210F PC5300	TT8020 TT8080 TT9030 TT9080	ACP3000 ACU2500 ACP200 ACP300	AH120 AH725 AH3135 AH130 AH3225 AH9130	PR1230 PR1535	HC844 CY25 CY250 CY259V JS4045	GC1030 GC1010 GC2030	KC525M KC530 KC725M KC735M KCPM40 KCSM30 X400
	P40		YBG302	VP30RT	PC5400	TT8020 TT8080 TT9030 TT9080	ACP3000 ACU2500 ACP300	AH140		PTH30E PTH40H JS4060 GX2140	GC1030 GC2030	KC725M KC735M KCPM40
	M10		YBG252		PC210F		ACU2500 ACM100 ACK300 ACP300	AH725	PR1025 PR1225	PN15M PN215	GC1010 GC1030	KC515M SP4019 SP6519
	M20	OP1202 OP1215 OP1205H	YBG202 YBG205 YBG9320 YBG252	VP15TF MP7130 MP7030 VP20RT	PC5300	TT9030 TT9080	ACU2500 ACK300 ACP300	AH725 AH3135 AH130 AH6030 AH3225 AH9130	PR1525 PR1025 PR1225	JP4120	GC1030 GC1040 GC2030 S30T	KC522M KC525M SP4019 SP6519 X700
	M30	OP1302	YBG302	VP15TF MP7130 MP7030 VP20RT MP7140	PC9530 PC5400	TT8020 TT8080 TT9030 TT9080	ACM300	AH3135 AH130 AH9130	PR1535	HC844 CY250 JS4045	GC1040 S30T GC2030	KC522M KC525M KC725M KC735M KCPM40 KCSM30 KCSM40 SC6525 X700
	M40		YBG302	MP7140 VP30RT	PC5400	TT8020 TT8080 TT9030 TT9080	ACM300	AH140		PTH30E PTH40H JM4160 GX2160 AX2040		KC725M KCPM40 KCSM40
	K10	OP1102	YBG102 YBG252	MP8010	PC8110 PC6510	TT6080	ACK3000 ACU2500	AH110 GH120	PR510 PR905 PR1210	ATH10E TH315 CY100H	GC1010 GC1020	KC514M KC515M KCK20 SP4019
	K20	OP1202 OP2212	YBG152	VP15TF VP20RT	PC5300	TT6080	ACK3000 ACU2500 ACK300	AH120 AH9030 AH9130	PR905 PR1210	CY9020 CY150 PTH13S JP4120 GX2120	GC1020	KC514M KC520M KC524M KCK20 SP6519
	K30	OP1205 OP1205H		VP15TF VP20RT			ACK3000 ACU2500 ACK300	AH120		CY250 JS4045 GX2040		KC522M KC524M SP6519

Hardness Comparison

Hardness				Tensile Strength
Rockwell	Hardness(RH)	Vickers Hardness(VH)	Brinell Hardness(BH)	
HRC	HRA	HV	HB	
70.0	86.6	1037		
69.5	86.3	1017		
69.0	86.1	997		
68.5	85.8	978		
68.0	85.5	959		
67.5	85.2	941		
67.0	85.0	923		
66.5	84.7	906		
66.0	84.4	889		
65.5	84.1	872		
65.0	83.9	856		
64.5	83.6	840		
64.0	83.3	825		
63.5	83.1	810		
63.0	82.8	795		
62.5	82.5	780		
62.0	82.2	766		
61.5	82.0	752		
61.0	81.7	739		
60.5	81.4	726		
60.0	81.2	713		2555
59.5	80.9	700		2500
59.0	80.6	688		2450
58.5	80.3	676		2395
58.0	80.1	664		2345
57.5	79.8	653		2295
57.0	79.5	642		2250
56.5	79.3	631		2205
56.0	79.0	620		2160
55.5	78.7	609		2115
55.0	78.5	599		2075
54.5	78.2	589		2035
54.0	77.9	579		1995
53.5	77.7	570		1955
53.0	77.4	561		1920
52.5	77.1	551		1885
52.0	76.9	543		1850
51.5	76.6	534		1815

Hardness				Tensile Strength
Rockwell	Hardness(RH)	Vickers Hardness(VH)	Brinell Hardness(BH)	
HRC	HRA	HV	HB	
51.0	76.3	501		1780
50.5	76.1	494		1750
50.0	75.8	488		1720
49.5	75.5	481		1690
49.0	75.3	474		1660
48.5	75.0	468		1630
48.0	74.7	461		1605
47.5	74.5	455		1575
47.0	74.2	449		1550
46.5	73.9	442		1525
46.0	73.7	436		1500
45.5	73.4	430		1475
45.0	73.2	424		1450
44.5	72.9	418		1430
44.0	72.6	413		1405
43.5	72.4	407		1385
43.0	72.1	401		1360
42.5	71.8	396		1340
42.0	71.6	391		1320
41.5	71.3	385		1300
41.0	71.1	380		1280
40.5	70.8	375		1260
40.0	70.5	370		1245
39.5	70.3	365		1225
39.0	70.0	360		1210
38.5		355		1190
38.0		350		1175
37.5		345		1160
37.0		341		1140
36.5		336		1125
36.0		332		1110
35.5		327		1095
35.0		323		1080
34.5		318		1065
34.0		314		1050
33.5		310		1035
33.0		306		1020
32.5		302		1010

Hardness Comparison

Hardness				Tensile Strength
Rockwell	Hardness(RH)	Vickers Hardness(VH)	Brinell Hardness(BH)	
HRC	HRA	HV	HB	
32.0		304	298	995
31.5		300	294	980
31.0		296	291	970
30.5		292	287	960
30.0		289	283	950
29.5		285	280	935
29.0		281	276	920
28.5		278	273	910
28.0		274	269	900
27.5		271	266	890
27.0		268	263	880
26.5		264	260	870
26.0		261	257	860
25.5		258	254	850
25.0		255	251	835
24.5		252	248	830

Hardness				Tensile Strength
Rockwell	Hardness(RH)	Vickers Hardness(VH)	Brinell Hardness(BH)	
HRC	HRA	HV	HB	
24.0		249	245	820
23.5		246	242	810
23.0		243	240	800
22.5		240	237	790
22.0		237	234	785
21.5		234	232	775
21.0		231	229	765
20.5		229	227	760
20.0		226	225	750
19.5		223	222	745
19.0		221	220	735
18.5		218	218	730
18.0		216	216	725
17.5		214	214	715
17.0		211	211	710